

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property Organization  
International Bureau



(43) International Publication Date  
11 October 2001 (11.10.2001)

PCT

(10) International Publication Number  
**WO 01/74941 A1**

(51) International Patent Classification<sup>7</sup>: C08L 25/02,  
25/14, 31/02, 31/04, 33/02, 33/04, 39/00, 39/08

(21) International Application Number: PCT/US01/09333

(22) International Filing Date: 22 March 2001 (22.03.2001)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:  
09/540,033 31 March 2000 (31.03.2000) US

(81) Designated States (*national*): AL, AM, AT, AU, AZ, BB, BG, BR, BY, CA, CH, CN, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IS, JP, KE, KG, KP, KR, KZ, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, UZ, VN.

(84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

(71) Applicant: NATIONAL STARCH & CHEMICAL COMPANY [US/US]; 10 Finderne Avenue, Bridgewater, NJ 08807 (US).

**Published:**

- with international search report
- before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments

(72) Inventor: EKNOIAN, Michael, W.; 8 Birchmont Lane, Warren, NJ 07059 (US).

(74) Agent: MUCCINO, Richard, R.; 758 Springfield Avenue, Summit, NJ 07901 (US).

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

(54) Title: SALT SENSITIVE AQUEOUS EMULSIONS

(57) Abstract: This invention relates to aqueous emulsions comprising a water-dispersible copolymer which is non-dispersible in aqueous solutions containing 0.5% or more of an inorganic salt, comprising acidic ethylenically unsaturated monomers and ethylenically unsaturated monomers. The acidic ethylenically unsaturated monomers and the ethylenically unsaturated monomers are defined herein. The present invention also pertains to emulsion polymerization methods for making the aqueous emulsions with or without a surfactant.

BEST AVAILABLE COPY

WO 01/74941 A1

5

## Salt Sensitive Aqueous Emulsions

### Field of the Invention

10

This invention relates to aqueous emulsions comprising a water-dispersible copolymer which is non-dispersible in aqueous solutions containing 0.5% or more of an inorganic salt, comprising acidic ethylenically unsaturated monomers and ethylenically unsaturated monomers. The acidic ethylenically unsaturated monomers and the ethylenically unsaturated monomers are defined herein. The present invention also pertains to emulsion polymerization methods for making the aqueous emulsions with or

15

without a surfactant.

### Background of The Invention

5           Water-soluble polymers, soluble in tap water but insoluble in dilute salt solutions, are known in the art, however many of these water-soluble polymer compositions are not entirely satisfactory. Moreover, many water-soluble copolymers require alkali to remove the polymeric film which is often difficult and unsafe for the consumer. The present invention provides  
10   improved water-dispersible copolymer compositions without the disadvantages characteristic of previously known compositions.

### SUMMARY OF THE INVENTION

15           In a first embodiment, the present invention is directed to an aqueous emulsion comprising a water-dispersible copolymer which is non-dispersible in aqueous solutions containing 0.5% or more of an inorganic salt, wherein the water-dispersible copolymer comprises in percentages by weight:

20           (A) from about 10% to about 90% of an acidic ethylenically unsaturated monomer; and

          (B) from about 10% to about 90% of an ethylenically unsaturated monomer selected from the group of monomer formulas consisting of:

- (i)  $\text{CH}_2=\text{C}(\text{R}_1)\text{COR}_2$ ;
- (ii)  $\text{R}_3\text{OOC}-\text{CH}=\text{CH}-\text{COOR}_4$ ;
- (iii)  $\text{CH}_2=\text{C}(\text{R}_5)\text{OCOR}_6$ ;
- (iv)  $\text{CH}_2=\text{C}(\text{COOR}_7)\text{CH}_2\text{COOR}_8$ ;
- (v)  $\text{CH}_3\text{CH}=\text{CHCOOR}_9$ ;
- (vi)  $\text{R}_{10}\text{C}_6\text{H}_4\text{CR}_{11}=\text{CHR}_{11}$ ; and
- (vii)  $\text{R}_{12}\text{CH}=\text{CHR}_{13}$ ;

wherein  $\text{R}_1$  is hydrogen or methyl and  $\text{R}_2$  is  $-\text{OZ}'$  or  $-\text{N}(\text{Z}'')(\text{Z}''')$ , wherein  $\text{Z}'$  is an alkyl group having from 1 to 7 carbon atoms, and  $\text{Z}''$  is independently selected from the group consisting of hydrogen and alkyl groups having from 1 to 6 carbon atoms;  $\text{R}_3$  and  $\text{R}_4$  are independently hydrogen or an alkyl group having from 1 to 7 carbon atoms, with the proviso that  $\text{R}_3$  and  $\text{R}_4$  are not both hydrogen;  $\text{R}_5$  is hydrogen or methyl and  $\text{R}_6$  is an alkyl group having from 1 to 7 carbon atoms;  $\text{R}_7$  and  $\text{R}_8$  are independently hydrogen or an alkyl group having from 1 to 7 carbon atoms, with the proviso that  $\text{R}_7$  and  $\text{R}_8$  are not both hydrogen;  $\text{R}_9$  is an alkyl group having from 1 to 7 carbon atoms;  $\text{R}_{10}$  and  $\text{R}_{11}$  are hydrogen;  $\text{R}_{12}$  and  $\text{R}_{13}$  are independently selected from the group consisting of hydrogen,  $-\text{CN}$ ,  $-\text{NHCHO}$ ,  $-\text{NHCOCH}_3$ , and an alkyl group having from 1 to 7 carbon atoms; and the copolymer has a weight average molecular weight greater than about 25,000 and is present in an amount from about 20% to about 70%.

In a second embodiment, the present invention is directed to an aqueous emulsion comprising a water-dispersible copolymer which is non-dispersible in aqueous solutions containing 0.5% or more of an inorganic salt, wherein the water-dispersible copolymer comprises in percentages by weight:

(A) from about 10% to about 90% of an acidic ethylenically unsaturated monomer; and

(B) from about 10% to about 90% of an ethylenically unsaturated monomer selected from the group of monomer formulas consisting of:

- (i)  $\text{CH}_2=\text{C}(\text{R}'_1)\text{COR}'_2$ ;
- (ii)  $\text{R}'_3\text{OOC}-\text{CH}=\text{CH}-\text{COOR}'_4$ ;
- (iii)  $\text{CH}_2=\text{C}(\text{R}'_5)\text{OCOR}'_6$ ;
- (iv)  $\text{CH}_2=\text{C}(\text{COOR}'_7)\text{CH}_2\text{COOR}'_8$ ;
- (v)  $\text{CH}_3\text{CH}=\text{CHCOOR}'_9$ ;
- (vi)  $\text{R}'_{10}\text{C}_6\text{H}_4\text{CR}'_{11}=\text{CHR}'_{11}$ ; and
- (vii)  $\text{R}'_{12}\text{CH}=\text{CHR}'_{13}$ ;

wherein  $\text{R}'_1$  is hydrogen or methyl, and  $\text{R}'_2$  is selected from the group consisting of  $-\text{OZ}'$ ,  $-\text{N}(\text{Z}'')(\text{Z}'')$ , and  $-\text{OZ}'''\text{OH}$ , wherein  $\text{Z}'$  is an alkyl group having from 8 to 18 carbon atoms;  $\text{Z}''$  is independently selected from the group consisting of alkyl groups having from 7 to 10 carbon atoms, dimethylamino alkyl groups having from 1 to 5 carbon atoms, and hydroxyalkyl groups having from 1 to 5 carbon atoms; and  $\text{Z}'''$  is an alkyl group having from 1 to 4 carbon atoms;  $\text{R}'_3$  and  $\text{R}'_4$  are independently an

alkyl group having from 8 to 18 carbon atoms; R'<sub>5</sub> is hydrogen or methyl and R'<sub>6</sub> is an alkyl group having from 8 to 18 carbon atoms; R'<sub>7</sub> and R'<sub>8</sub> are independently an alkyl group having from 8 to 18 carbon atoms; R'<sub>9</sub> is an alkyl group having from 8 to 18 carbon atoms; R'<sub>10</sub> and R'<sub>11</sub> are  
5 independently an alkyl group having from 1 to 2 carbon atoms; R'<sub>12</sub> and R'<sub>13</sub> are independently selected from the group consisting of 2-pyrrolidinone, N-caprolactam, 2-pyridine, 3-pyridine, 4-pyridine, and an alkyl group having from 7 to 18 carbon atoms, with the proviso that R'<sub>12</sub> and R'<sub>13</sub> are not at the same time 2-pyrrolidinone, N-caprolactam, 2-pyridine, 3-pyridine, or 4-  
10 pyridine; and the copolymer has a weight average molecular weight greater than about 25,000 and is present in an amount from about 20% to about 70%.

In a third embodiment, the present invention is directed to an  
15 aqueous emulsion comprising a water-dispersible copolymer which is non-dispersible in aqueous solutions containing 0.5% or more of an inorganic salt, wherein the water-dispersible copolymer comprises in percentages by weight:

(A) from about 10% to about 80% of an acidic ethylenically unsaturated  
20 monomer, with the proviso that the acidic ethylenically unsaturated monomer is not acrylic acid;



(B) from about 10% to about 80% of an ethylenically unsaturated monomer selected from the group of monomer formulas consisting of:

- (i)  $\text{CH}_2=\text{C}(\text{R}_1)\text{COR}_2$ ;
- (ii)  $\text{R}_3\text{OOC}-\text{CH}=\text{CH}-\text{COOR}_4$ ;
- (iii)  $\text{CH}_2=\text{C}(\text{R}_5)\text{OCOR}_6$ ;
- (iv)  $\text{CH}_2=\text{C}(\text{COOR}_7)\text{CH}_2\text{COOR}_8$ ;
- 5 (v)  $\text{CH}_3\text{CH}=\text{CHCOOR}_9$ ;
- (vi)  $\text{R}_{10}\text{C}_6\text{H}_4\text{CR}_{11}=\text{CHR}_{11}$ ; and
- (vii)  $\text{R}_{12}\text{CH}=\text{CHR}_{13}$ ;

wherein  $\text{R}_1$  is hydrogen or methyl and  $\text{R}_2$  is  $-\text{OZ}'$  or  $-\text{N}(\text{Z}'')(\text{Z}'')$ , wherein  $\text{Z}'$  is an alkyl group having from 1 to 7 carbon atoms, and  $\text{Z}''$  is independently  
 10 selected from the group consisting of hydrogen and alkyl groups having from 1 to 6 carbon atoms;  $\text{R}_3$  and  $\text{R}_4$  are independently hydrogen or an alkyl group having from 1 to 7 carbon atoms, with the proviso that  $\text{R}_3$  and  $\text{R}_4$  are not both hydrogen;  $\text{R}_5$  is hydrogen or methyl and  $\text{R}_6$  is an alkyl group having from 1 to 7 carbon atoms;  $\text{R}_7$  and  $\text{R}_8$  are independently hydrogen or an alkyl  
 15 group having from 1 to 7 carbon atoms, with the proviso that  $\text{R}_7$  and  $\text{R}_8$  are not both hydrogen;  $\text{R}_9$  is an alkyl group having from 1 to 7 carbon atoms;  $\text{R}_{10}$  and  $\text{R}_{11}$  are hydrogen; and  $\text{R}_{12}$  and  $\text{R}_{13}$  are independently selected from the group consisting of hydrogen,  $-\text{CN}$ ,  $-\text{NHCHO}$ , and an alkyl group having from 1 to 7 carbon atoms; and

20 (C) from about 10% to about 80% of an ethylenically unsaturated monomer selected from the group of monomer formulas consisting of:

- (i)  $\text{CH}_2=\text{C}(\text{R}'_1)\text{COR}'_2$ ;



wherein  $\text{R}'_1$  is hydrogen or methyl, and  $\text{R}'_2$  is selected from the group consisting of  $-\text{OZ}'$ ,  $-\text{N}(\text{Z}'')(\text{Z}'')$ , and  $-\text{OZ}'''\text{OH}$ , wherein  $\text{Z}'$  is an alkyl group having from 8 to 18 carbon atoms;  $\text{Z}''$  is independently selected from the group consisting of alkyl groups having from 7 to 10 carbon atoms, dimethylamino alkyl groups having from 1 to 5 carbon atoms, and hydroxyalkyl groups having from 1 to 5 carbon atoms; and  $\text{Z}'''$  is an alkyl group having from 1 to 4 carbon atoms;  $\text{R}'_3$  and  $\text{R}'_4$  are independently an alkyl group having from 8 to 18 carbon atoms;  $\text{R}'_5$  is hydrogen or methyl and  $\text{R}'_6$  is an alkyl group having from 8 to 18 carbon atoms;  $\text{R}'_7$  and  $\text{R}'_8$  are independently an alkyl group having from 8 to 18 carbon atoms;  $\text{R}'_9$  is an alkyl group having from 8 to 18 carbon atoms;  $\text{R}'_{10}$  and  $\text{R}'_{11}$  are independently an alkyl group having from 1 to 2 carbon atoms;  $\text{R}'_{12}$  and  $\text{R}'_{13}$  are independently selected from the group consisting of 2-pyrrolidinone, N-caprolactam, and an alkyl group having from 7 to 18 carbon atoms, with the proviso that  $\text{R}_{12}$  and  $\text{R}_{13}$  are not both 2-pyrrolidinone, are not both N-caprolactam, or are not a mixture thereof; and the copolymer has a weight average molecular weight greater than about 25,000 and is present in an



amount from about 20% to about 70%.

The present invention is also directed to methods for preparing the aqueous emulsions in the above embodiments. A first method comprises the steps of (a) providing the monomers in one of the above embodiments; and (b) emulsion polymerizing the monomers in water at a solids level from about 20% to about 70% in the presence of a surfactant. A second method comprises the steps of (a) providing the monomers in one of the above embodiments; (b) neutralizing the monomers in water to a level from about 2% to about 15% molar of the acidic ethylenically unsaturated monomer from (A); and (c) emulsion polymerizing the monomers at a solids level from about 20% to about 60% without a surfactant.

#### DETAILED DESCRIPTION OF THE INVENTION

15

In accord with the present invention, aqueous emulsions comprising water-dispersible copolymers are provided that are non-dispersible in dilute inorganic salt solutions. The salt-sensitive copolymers are soluble/dispersible in tap water but are non-dispersible in water containing at least 0.5% of an inorganic monovalent, divalent, or trivalent salt. The water-dispersible copolymers are prepared from acidic ethylenically unsaturated monomers and a variety of other ethylenically unsaturated monomers. By carefully selecting the type and amount of the acidic ethylenically

unsaturated monomer, one can obtain copolymer products having good hydrophilic properties such that the copolymer is water-dispersible, especially when partially neutralized, but is non-dispersible in dilute inorganic salt solutions. By carefully selecting the type and amount of the other ethylenically unsaturated monomers, one can obtain copolymer products useful for non-woven fabrics or papers having good wet strength and permeability to body fluids. The water-dispersible copolymers may be employed in protective top coats, floor polishes, temporary printing, adhesives, skin creams, sun screens, hair fixatives, temporary decorative paints, marine coatings, repulpable paper coatings, glass fiber sizing, time release/erodible coatings or particles, and antiperspirant-film not removed by perspiration but removed by soap and water.

Unlike conventional water-soluble polymers, the aqueous emulsions of the present invention do not require divalent ion inhibitors. Film formation of latexes differs from film formation of solution polymers since particle coalescence is needed to form a film of high cohesive strength in emulsion polymers. For solution polymers, particle coalescence is not necessary because the solvent acts as a plasticizer which aids in the film formation by allowing polymer chains to mix and entangle. For emulsion polymers, the cohesive strength of the polymer film is reduced if the particles do not fully coalesce because of the reduction of chain entanglements. For emulsion polymers, the surface active layer remains as an interfacial boundary

between particles and prevents full chain entanglement to the extent observed from solution polymers. As a result, films derived from the aqueous emulsions of the present invention will readily disperse in the presence of water. In addition, the novel polymer film will also disperse in  
5 hard water since divalent ions do not inhibit the redispersability by the film derived from emulsions. In contrast, for polymer films derived solution, hard water is less effective in solubilizing the polymer since divalent ions inhibit the movement of the highly entangled polymer chains. For films derived from solution polymers, ion regulating agents are required to enhance the  
10 solubilization in hard water. This is the main reason why the aqueous emulsions of the present invention do not require a divalent ion inhibitor (sequestering agent) to aid in the redispersability in tap water, especially hard water. Preferably the particle size of the water-dispersible copolymer is from about 0.05 micron to about 0.8 micron.

15

The present invention also provides emulsion polymerization methods to form stable, low viscosity, emulsions of the water-dispersible copolymers both with the use of surfactants and without the use of surfactants (in situ stabilization). In the surfactant embodiment, a seeded or  
20 unseeded process is utilized to copolymerize an acidic ethylenically unsaturated monomer, such as an unsaturated carboxylic acid monomer, and other ethylenically unsaturated monomers, such as alkyl (meth)acrylate(s) or vinyl monomer(s), in water with a surfactant. In the non-

surfactant embodiment, the monomers are first neutralized in water to a level from about 2% to about 15% molar of the acidic ethylenically unsaturated monomer, and the resulting emulsion is then polymerized without a surfactant. In a preferred (non-surfactant) method, a seed polymer  
5 is polymerized in water with the first stage comprising the acidic ethylenically unsaturated monomer, and other ethylenically unsaturated monomers, which are at least partially neutralized (10% to 100%) with aqueous ammonia to form the in situ stabilizer colloid. In the second stage, this colloid is copolymerized with 100 parts of an ethylenically unsaturated  
10 monomer, such as acrylic monomers like 2-ethyl hexyl acrylate, styrene, butyl acrylate, ethyl acrylate, acrylic acid, methacrylic acid, etc. and/or vinyl acetate, monoethyl maleate, maleic acid, itaconic acid, etc. When the emulsions are dried, the resulting film particles are dispersible in water since the copolymer contains a high concentration of hydrophilic monomers, such  
15 as acidic functionality. This acidic functionality also prevents the particles from dispersing in aqueous salt solutions. To further improve water dispersability, a chain transfer agent, or polymerization terminator, such as dodecyl mercaptan, may be added to reduce the molecular weight of the polymer during the polymerization process. Typical emulsion  
20 polymerizations are batch, semi-batch, slow-addition, and continuous processes. Monomers can be slow added linearly, or via gradient simultaneously, or separately.

As set out above, the salt-sensitive copolymers are soluble/dispersible in tap water but are non-dispersible in water containing at least 0.5% of an inorganic monovalent, divalent, or trivalent metal salt.

5 Examples of monovalent inorganic metal salts include sodium chloride, potassium phosphate, and sodium acetate. Examples of divalent inorganic metal salts include magnesium chloride, barium chloride, calcium chloride, calcium carbonate, and magnesium acetate. Examples of trivalent inorganic metal salts include aluminum chloride, boron chloride, and aluminum

10 acetate.

The term "alkyl group", as used herein, refers to branched or unbranched hydrocarbon groups as well as cyclic and bicyclic hydrocarbon groups. The term halogen, as used herein, refers to the chemically related

15 elements consisting of fluorine, chlorine, bromine and iodine.

In a first embodiment, the present invention is directed to an aqueous emulsion comprising a water-dispersible copolymer which is non-dispersible in aqueous solutions containing 0.5% or more of an inorganic

20 salt, wherein the water-dispersible copolymer comprises in percentages by weight:

(A) from about 10% to about 90% of an acidic ethylenically unsaturated monomer; and

(B) from about 10% to about 90% of an ethylenically unsaturated monomer selected from the group of monomer formulas consisting of:

- (i)  $\text{CH}_2=\text{C}(\text{R}_1)\text{COR}_2$ ;
- (ii)  $\text{R}_3\text{OOC}-\text{CH}=\text{CH}-\text{COOR}_4$ ;
- (iii)  $\text{CH}_2=\text{C}(\text{R}_5)\text{OCOR}_6$ ;
- (iv)  $\text{CH}_2=\text{C}(\text{COOR}_7)\text{CH}_2\text{COOR}_8$ ;
- (v)  $\text{CH}_3\text{CH}=\text{CHCOOR}_9$ ;
- (vi)  $\text{R}_{10}\text{C}_6\text{H}_4\text{CR}_{11}=\text{CHR}_{11}$ ; and
- (vii)  $\text{R}_{12}\text{CH}=\text{CHR}_{13}$ ;

wherein  $\text{R}_1$  is hydrogen or methyl and  $\text{R}_2$  is  $-\text{OZ}'$  or  $-\text{N}(\text{Z}'')(\text{Z}''')$ , wherein  $\text{Z}'$  is an alkyl group having from 1 to 7 carbon atoms, and  $\text{Z}''$  is independently selected from the group consisting of hydrogen and alkyl groups having from 1 to 6 carbon atoms;  $\text{R}_3$  and  $\text{R}_4$  are independently hydrogen or an alkyl group having from 1 to 7 carbon atoms, with the proviso that  $\text{R}_3$  and  $\text{R}_4$  are not both hydrogen;  $\text{R}_5$  is hydrogen or methyl and  $\text{R}_6$  is an alkyl group having from 1 to 7 carbon atoms;  $\text{R}_7$  and  $\text{R}_8$  are independently hydrogen or an alkyl group having from 1 to 7 carbon atoms, with the proviso that  $\text{R}_7$  and  $\text{R}_8$  are not both hydrogen;  $\text{R}_9$  is an alkyl group having from 1 to 7 carbon atoms;  $\text{R}_{10}$  and  $\text{R}_{11}$  are hydrogen;  $\text{R}_{12}$  and  $\text{R}_{13}$  are independently selected from the group consisting of hydrogen,  $-\text{CN}$ ,  $-\text{NHCHO}$ ,  $-\text{NHCOCH}_3$ , and an alkyl group having from 1 to 7 carbon atoms; and the copolymer has a weight average molecular weight greater than about 25,000 and is present in an amount from about 20% to about 70%.

In this embodiment, the acidic ethylenically unsaturated monomers from (A) may be selected from the group consisting of monomers containing a carboxylic acid group, monomers containing a sulfonic acid group, and monomers containing a phosphoric acid group. Examples of monomers containing a carboxylic acid group may be selected from the group consisting of acrylic acid, methacrylic acid, maleic acid, maleic acid half esters, maleic anhydride, itaconic acid, and crotonic acid. Preferably, the monomer containing a carboxylic acid group is methacrylic acid. Examples of monomers containing a sulfonic acid group may be selected from the group consisting of styrene sulfonic acid, 2-acrylamido-2-methylpropane sulfonic acid, and sodium vinyl sulfonate. Preferably, the monomer containing a sulfonic acid group is styrene sulfonic acid or 2-acrylamido-2-methylpropane sulfonic acid. Examples of monomers containing a phosphoric acid group may be selected from the group consisting of styrene phosphoric acid, sodium vinyl phosphonate, and  $\text{CH}_2=\text{C}(\text{CH}_3)\text{COO}(\text{CH}_2)_n\text{OPO}_3\text{H}$ , wherein  $n$  is from 2 to 4. Preferably, the monomer containing a phosphoric acid group is  $\text{CH}_2=\text{C}(\text{CH}_3)\text{COO}(\text{CH}_2)_n\text{OPO}_3\text{H}$ , wherein  $n$  is from 2 to 4.

20

Preferably, the ethylenically unsaturated monomer from (B) is (i)  $\text{CH}_2=\text{C}(\text{R}_1)\text{COR}_2$ , wherein  $\text{R}_1$  is methyl and  $\text{R}_2$  is  $-\text{OZ}'$ , wherein  $\text{Z}'$  is an alkyl group having from 1 to 4 carbon atoms. Examples of the ethylenically

unsaturated monomer from (B) (i),  $\text{CH}_2=\text{C}(\text{R}_1)\text{COR}_2$ , may be selected from the group of (meth)acrylamides consisting of (meth)acrylamide, N-methyl (meth)acrylamide, N-ethyl (meth)acrylamide, N-propyl (meth)acrylamide, N-butyl (meth)acrylamide, N-pentyl (meth)acrylamide, N-hexyl (meth)acrylamide, N-heptyl (meth)acrylamide, N,N-dimethyl (meth)acrylamide, N,N-diethyl (meth)acrylamide, N,N-dipropyl (meth)acrylamide, and N,N-dibutyl (meth)acrylamide. Other examples of the ethylenically unsaturated monomer from (B) (i),  $\text{CH}_2=\text{C}(\text{R}_1)\text{COR}_2$ , may be selected from the group of (meth)acrylates consisting of methyl (meth)acrylate, ethyl (meth)acrylate, propyl (meth)acrylate, butyl (meth)acrylate, pentyl (meth)acrylate, hexyl (meth)acrylate, heptyl (meth)acrylate, dimethyl (meth)acrylate, diethyl (meth)acrylate, dipropyl (meth)acrylate, and dibutyl (meth)acrylate.

15 Preferably, the ethylenically unsaturated monomer from (B) is (ii)  $\text{R}_3\text{OOC}-\text{CH}=\text{CH}-\text{COOR}_4$ , wherein  $\text{R}_3$  and  $\text{R}_4$  are independently an alkyl group having from 1 to 4 carbon atoms, more preferably from 2 to 4 carbon atoms.

20 Preferably, the ethylenically unsaturated monomer from (B) is (iii)  $\text{CH}_2=\text{C}(\text{R}_5)\text{OCOR}_6$ , wherein  $\text{R}_5$  is methyl and  $\text{R}_6$  is an alkyl group having from 1 to 4 carbon atoms. Examples of the ethylenically unsaturated monomer from (B) (iii),  $\text{CH}_2=\text{C}(\text{R}_5)\text{OCOR}_6$ , may be selected from the group



consisting of vinyl formate, vinyl acetate, vinyl propionate, vinyl isobutyrate, and vinyl pivalate.

Preferably, the ethylenically unsaturated monomer from (B) is (iv)  
5  $\text{CH}_2=\text{C}(\text{COOR}_7)\text{CH}_2\text{COOR}_8$ , wherein  $\text{R}_7$  and  $\text{R}_8$  are independently an alkyl group having from 1 to 4 carbon atoms, more preferably from 2 to 4 carbon atoms. Preferably, the ethylenically unsaturated monomer from (B) is (v)  $\text{CH}_3\text{CH}=\text{CHCOOR}_9$ , wherein  $\text{R}_9$  is an alkyl group having from 1 to 4 carbon atoms, more preferably from 2 to 4 carbon atoms. Preferably, the  
10 ethylenically unsaturated monomer from (B) is (vi) styrene.

Preferably, the ethylenically unsaturated monomer from (B) is (vii)  $\text{R}_{12}\text{CH}=\text{CHR}_{13}$ , wherein  $\text{R}_{12}$  and  $\text{R}_{13}$  are independently hydrogen or methyl. Examples of the ethylenically unsaturated monomer from (B) (vii),  
15  $\text{R}_{12}\text{CH}=\text{CHR}_{13}$ , may be selected from the group consisting of ethylene, propylene, butylene, butadiene, acrylonitrile, N-vinyl formamide, and vinyl acetamide.


In this embodiment, the exact amount of acidic ethylenically  
20 unsaturated monomer from (A) and ethylenically unsaturated monomer from (B) present in the water-dispersible copolymer is a matter of preference subject to such factors as the particular type of ethylenically unsaturated monomer employed, the molecular weight of the water-dispersible


copolymer employed, and are particular to the end use application. In a preferred embodiment, the acidic ethylenically unsaturated monomer from (A) is present in the water-dispersible copolymer in an amount from about 10% to about 90%, preferably from about 25% to about 75%, more preferably from about 30% to about 70%, and most preferably from about 35% to about 65%, by weight. In a preferred embodiment, the ethylenically unsaturated monomer from (B) is present in the water-dispersible copolymer in an amount from about 10% to about 90%, preferably from about 25% to about 75%, more preferably from about 30% to about 70%, and most preferably from about 35% to about 65%, by weight.

In a second embodiment, the present invention is directed to an aqueous emulsion comprising a water-dispersible copolymer which is non-dispersible in aqueous solutions containing 0.5% or more of an inorganic salt, wherein the water-dispersible copolymer comprises in percentages by weight:

(A) from about 10% to about 90% of an acidic ethylenically unsaturated monomer; and

(B) from about 10% to about 90% of an ethylenically unsaturated monomer selected from the group of monomer formulas consisting of:





wherein  $\text{R}'_1$  is hydrogen or methyl, and  $\text{R}'_2$  is selected from the group consisting of  $-\text{OZ}'$ ,  $-\text{N}(\text{Z}'')(\text{Z}'')$ , and  $-\text{OZ}'''\text{OH}$ , wherein  $\text{Z}'$  is an alkyl group having from 8 to 18 carbon atoms;  $\text{Z}''$  is independently selected from the group consisting of alkyl groups having from 7 to 10 carbon atoms,  
 10 dimethylamino alkyl groups having from 1 to 5 carbon atoms, and hydroxyalkyl groups having from 1 to 5 carbon atoms; and  $\text{Z}'''$  is an alkyl group having from 1 to 4 carbon atoms;  $\text{R}'_3$  and  $\text{R}'_4$  are independently an alkyl group having from 8 to 18 carbon atoms;  $\text{R}'_5$  is hydrogen or methyl and  $\text{R}'_6$  is an alkyl group having from 8 to 18 carbon atoms;  $\text{R}'_7$  and  $\text{R}'_8$  are  
 15 independently an alkyl group having from 8 to 18 carbon atoms;  $\text{R}'_9$  is an alkyl group having from 8 to 18 carbon atoms;  $\text{R}'_{10}$  and  $\text{R}'_{11}$  are independently an alkyl group having from 1 to 2 carbon atoms;  $\text{R}'_{12}$  and  $\text{R}'_{13}$  are independently selected from the group consisting of 2-pyrrolidinone, N-caprolactam, 2-pyridine, 3-pyridine, 4-pyridine, and an alkyl group having  
 20 from 7 to 18 carbon atoms, with the proviso that  $\text{R}_{12}$  and  $\text{R}_{13}$  are not at the same time 2-pyrrolidinone, N-caprolactam, 2-pyridine, 3-pyridine, or 4-pyridine; and the copolymer has a weight average molecular weight greater than about 25,000 and is present in an amount from about 20% to about

70%.

The acidic ethylenically unsaturated monomers from (A) in this embodiment are as defined above.

5

Preferably, the ethylenically unsaturated monomer from (B) is (i)  $\text{CH}_2=\text{C}(\text{R}'_1)\text{COR}'_2$ , wherein  $\text{R}'_1$  is methyl,  $\text{R}'_2$  is selected from the group consisting of  $-\text{OZ}'$ ,  $-\text{N}(\text{Z}'')(\text{Z}'')$ , and  $-\text{OZ}'''\text{OH}$ , wherein  $\text{Z}'$  is an alkyl group having from 8 to 12 carbon atoms, preferably from 9 to 11 carbon atoms;  $\text{Z}''$  is independently selected from the group consisting of alkyl groups having from 8 to 10 carbon atoms, dimethylamino alkyl groups having from 1 to 3 carbon atoms, and hydroxyalkyl groups having from 1 to 3 carbon atoms; and  $\text{Z}'''$  is an alkyl group having from 1 to 2 carbon atoms. Examples of the ethylenically unsaturated monomer from (B) (i),  $\text{CH}_2=\text{C}(\text{R}'_1)\text{COR}'_2$ , may be selected from the group of (meth)acrylamides consisting of N-t-octyl (meth)acrylamide, N,N-di-t-octyl (meth)acrylamide, 2-(dimethylamino)ethyl (meth)acrylate, N-[3-(dimethylamino)propyl] (meth)acrylamide, N-(hydroxymethyl) (meth)acrylamide, and N-(isobutoxymethyl)acrylamide. Other examples of the ethylenically unsaturated monomer from (B) (i),  $\text{CH}_2=\text{C}(\text{R}'_1)\text{COR}'_2$ , may be selected from the group of (meth)acrylates consisting of 2-ethyl hexyl (meth)acrylate, octyl (meth)acrylate, t-octyl (meth)acrylate, nonyl (meth)acrylate, decyl (meth)acrylate, isobornyl (meth)acrylate, lauryl (meth)acrylate, and steryl (meth)acrylate. Other

10

15

20

examples of the ethylenically unsaturated monomer from (B) (i),  $\text{CH}_2=\text{C}(\text{R}'_1)\text{COR}'_2$ , may be selected from the group of hydroxy (meth)acrylates consisting of 1-hydroxymethyl (meth)acrylate, 2-hydroxymethyl (meth)acrylate, 1-hydroxyethyl (meth)acrylate, 2-hydroxyethyl (meth)acrylate, 1-hydroxypropyl (meth)acrylate, 2-hydroxypropyl (meth)acrylate, and 3-hydroxypropyl (meth)acrylate.

Preferably, the ethylenically unsaturated monomer from (B) is (ii)  $\text{R}'_3\text{OOC-CH=CH-COOR}'_4$ , wherein  $\text{R}'_3$  and  $\text{R}'_4$  are independently an alkyl group having from 8 to 12 carbon atoms, preferably from 9 to 11 carbon atoms.

Preferably, the ethylenically unsaturated monomer from (B) is (iii)  $\text{CH}_2=\text{C}(\text{R}'_5)\text{OCOR}'_6$ , wherein  $\text{R}'_5$  is methyl, and  $\text{R}'_6$  is an alkyl group having from 8 to 12 carbon atoms, preferably from 9 to 11 carbon atoms. Examples of the ethylenically unsaturated monomer from (B) (iii),  $\text{CH}_2=\text{C}(\text{R}'_5)\text{OCOR}'_6$ , and is selected from the group consisting of vinyl 2-ethylhexonate, vinyl p-t-butyl benzoate, vinyl esters of versatic acid, vinyl laurate, and vinyl stearate.

Preferably, the ethylenically unsaturated monomer from (B) is (iv)  $\text{CH}_2=\text{C}(\text{COOR}'_7)\text{CH}_2\text{COOR}'_8$ , wherein  $\text{R}'_7$  and  $\text{R}'_8$  are independently an alkyl group having from 8 to 12 carbon atoms, preferably from 9 to 11 carbon atoms. Preferably, the ethylenically unsaturated monomer from (B) is (v)

$\text{CH}_3\text{CH}=\text{CHCOOR}'_9$ , and  $\text{R}'_9$  is an alkyl group having from 8 to 12 carbon atoms, preferably from 9 to 11 carbon atoms. Preferably, the ethylenically unsaturated monomer from (B) is (vi)  $\text{R}'_{10}\text{C}_6\text{H}_4\text{CR}'_{11}=\text{CHR}'_{11}$ , and  $\text{R}'_{10}$  and  $\text{R}'_{11}$  are independently methyl.

5

Preferably, the ethylenically unsaturated monomer from (B) is (vii)  $\text{R}'_{12}\text{CH}=\text{CHR}'_{13}$ , wherein  $\text{R}'_{12}$  and  $\text{R}'_{13}$  are independently selected from the group consisting of 2-pyrrolidinone, N-caprolactam, 2-pyridine, 3-pyridine, 4-pyridine, and an alkyl group having from 7 to 12 carbon atoms, preferably from 8 to 11 carbon atoms. Examples of the ethylenically unsaturated monomer from (B) (vii),  $\text{R}'_{12}\text{CH}=\text{CHR}'_{13}$ , and is independently selected from the group consisting of vinyl 2-pyrrolidinone, vinyl N-caprolactam, and an alkyl group having from 7 to 12 carbon atoms, preferably from 8 to 11 carbon atoms.

10

15

In this embodiment, the exact amount of acidic ethylenically unsaturated monomer from (A) and ethylenically unsaturated monomer from (B) present in the water-dispersible copolymer is a matter of preference subject to such factors as the particular type of ethylenically unsaturated monomer employed, the molecular weight of the water-dispersible copolymer employed, and are particular to the end use application. In a preferred embodiment, the acidic ethylenically unsaturated monomer from (A) is present in the water-dispersible copolymer in an amount from about

20


10% to about 90%, preferably from about 25% to about 75%, more preferably from about 30% to about 70%, and most preferably from about 35% to about 65%, by weight. In a preferred embodiment, the ethylenically unsaturated monomer from (B) is present in the water-dispersible copolymer  
5 in an amount from about 10% to about 90%, preferably from about 25% to about 75%, more preferably from about 30% to about 70%, and most preferably from about 35% to about 65%, by weight.

In a third embodiment, the present invention is directed to an  
10 aqueous emulsion comprising a water-dispersible copolymer which is non-dispersible in aqueous solutions containing 0.5% or more of an inorganic salt, wherein the water-dispersible copolymer comprises in percentages by weight:

(A) from about 10% to about 80% of an acidic ethylenically unsaturated  
15 monomer, with the proviso that the acidic ethylenically unsaturated monomer is not acrylic acid;




(B) from about 10% to about 80% of an ethylenically unsaturated monomer selected from the group of monomer formulas consisting of:

- 20 (i)  $\text{CH}_2=\text{C}(\text{R}_1)\text{COR}_2$ ;  
(ii)  $\text{R}_3\text{OOC}-\text{CH}=\text{CH}-\text{COOR}_4$ ;  
(iii)  $\text{CH}_2=\text{C}(\text{R}_5)\text{OCOR}_6$ ;  
(iv)  $\text{CH}_2=\text{C}(\text{COOR}_7)\text{CH}_2\text{COOR}_8$ ;



wherein  $\text{R}_1$  is hydrogen or methyl and  $\text{R}_2$  is  $-\text{OZ}'$  or  $-\text{N}(\text{Z}'')(\text{Z}''')$ , wherein  $\text{Z}'$  is  
 5 an alkyl group having from 1 to 7 carbon atoms, and  $\text{Z}''$  is independently  
 selected from the group consisting of hydrogen and alkyl groups having from  
 1 to 6 carbon atoms;  $\text{R}_3$  and  $\text{R}_4$  are independently hydrogen or an alkyl  
 group having from 1 to 7 carbon atoms, with the proviso that  $\text{R}_3$  and  $\text{R}_4$  are  
 not both hydrogen;  $\text{R}_5$  is hydrogen or methyl and  $\text{R}_6$  is an alkyl group having  
 10 from 1 to 7 carbon atoms;  $\text{R}_7$  and  $\text{R}_8$  are independently hydrogen or an alkyl  
 group having from 1 to 7 carbon atoms, with the proviso that  $\text{R}_7$  and  $\text{R}_8$  are  
 not both hydrogen;  $\text{R}_9$  is an alkyl group having from 1 to 7 carbon atoms;  $\text{R}_{10}$   
 and  $\text{R}_{11}$  are hydrogen; and  $\text{R}_{12}$  and  $\text{R}_{13}$  are independently selected from the  
 group consisting of hydrogen,  $-\text{CN}$ ,  $-\text{NHCHO}$ , and an alkyl group having  
 15 from 1 to 7 carbon atoms; and

(C) from about 10% to about 80% of an ethylenically unsaturated  
 monomer selected from the group of monomer formulas consisting of:





(vi)  $R'_{10}C_6H_4CR'_{11}=CHR'_{11}$ ; and

(vii)  $R'_{12}CH=CHR'_{13}$ ;

wherein  $R'_1$  is hydrogen or methyl, and  $R'_2$  is selected from the group consisting of  $-OZ'$ ,  $-N(Z'')(Z''')$ , and  $-OZ'''OH$ , wherein  $Z'$  is an alkyl group having from 8 to 18 carbon atoms;  $Z''$  is independently selected from the group consisting of alkyl groups having from 7 to 10 carbon atoms, dimethylamino alkyl groups having from 1 to 5 carbon atoms, and hydroxyalkyl groups having from 1 to 5 carbon atoms; and  $Z'''$  is an alkyl group having from 1 to 4 carbon atoms;  $R'_3$  and  $R'_4$  are independently an alkyl group having from 8 to 18 carbon atoms;  $R'_5$  is hydrogen or methyl and  $R'_6$  is an alkyl group having from 8 to 18 carbon atoms;  $R'_7$  and  $R'_8$  are independently an alkyl group having from 8 to 18 carbon atoms;  $R'_9$  is an alkyl group having from 8 to 18 carbon atoms;  $R'_{10}$  and  $R'_{11}$  are independently an alkyl group having from 1 to 2 carbon atoms;  $R'_{12}$  and  $R'_{13}$  are independently selected from the group consisting of 2-pyrrolidinone, N-caprolactam, and an alkyl group having from 7 to 18 carbon atoms, with the proviso that  $R'_{12}$  and  $R'_{13}$  are not both 2-pyrrolidinone, are not both N-caprolactam, or are not a mixture thereof; and the copolymer has a weight average molecular weight greater than about 25,000 and is present in an amount from about 20% to about 70%.

The acidic ethylenically unsaturated monomers from (A) in this embodiment are as defined above. The ethylenically unsaturated

monomers from (B) in this embodiment selected from the group of monomer formulas consisting of (i)  $\text{CH}_2=\text{C}(\text{R}_1)\text{COR}_2$ ; (ii)  $\text{R}_3\text{OOC}-\text{CH}=\text{CH}-\text{COOR}_4$ ; (iii)  $\text{CH}_2=\text{C}(\text{R}_5)\text{OCOR}_6$ ; (iv)  $\text{CH}_2=\text{C}(\text{COOR}_7)\text{CH}_2\text{COOR}_8$ ; (v)  $\text{CH}_3\text{CH}=\text{CHCOOR}_9$ ; (vi)  $\text{R}_{10}\text{C}_6\text{H}_4\text{CR}_{11}=\text{CHR}_{11}$ ; and (vii)  $\text{R}_{12}\text{CH}=\text{CHR}_{13}$  are as defined above. The

5 ethylenically unsaturated monomers from (C) in this embodiment selected from the group of monomer formulas consisting of (i)  $\text{CH}_2=\text{C}(\text{R}'_1)\text{COR}'_2$ ; (ii)  $\text{R}'_3\text{OOC}-\text{CH}=\text{CH}-\text{COOR}'_4$ ; (iii)  $\text{CH}_2=\text{C}(\text{R}'_5)\text{OCOR}'_6$ ; (iv)  $\text{CH}_2=\text{C}(\text{COOR}'_7)\text{CH}_2\text{COOR}'_8$ ; (v)  $\text{CH}_3\text{CH}=\text{CHCOOR}'_9$ ; (vi)  $\text{R}'_{10}\text{C}_6\text{H}_4\text{CR}'_{11}=\text{CHR}'_{11}$ ; and (vii)  $\text{R}'_{12}\text{CH}=\text{CHR}'_{13}$  are as defined above.

10

In this embodiment, the exact amount of acidic ethylenically unsaturated monomer from (A), ethylenically unsaturated monomer from (B), and ethylenically unsaturated monomer from (C) present in the water-dispersible copolymer is a matter of preference subject to such factors as the

15 particular type of ethylenically unsaturated monomer employed, the molecular weight of the water-dispersible copolymer employed, and are particular to the end use application. In a preferred embodiment, the acidic ethylenically unsaturated monomer from (A) is present in the water-dispersible copolymer in an amount from about 10% to about 80%, preferably from about 15% to about 70%, and more preferably from about

20 20% to about 60%, by weight. In a preferred embodiment, the ethylenically unsaturated monomer from (B) is present in the water-dispersible copolymer in an amount from about 10% to about 80%, preferably from about 15% to

about 70%, and more preferably from about 20% to about 60%, by weight. In a preferred embodiment, the ethylenically unsaturated monomer from (C) is present in the water-dispersible copolymer in an amount from about 10% to about 80%, preferably from about 15% to about 70%, more preferably  
5 from about 20% to about 60%, and most preferably from about 25% to about 50%, by weight.

When the amount of the acidic ethylenically unsaturated monomer from (A) exceeds the amounts set out above, the strength of the copolymer  
10 is insufficient when it is wet with a body fluid. When the amount of the acidic ethylenically unsaturated monomer from (A) is less than the amounts set out above, the dispersibility of the copolymer in water is insufficient. When the amount of the ethylenically unsaturated monomer from (B) or (C) exceeds the amounts set out above, the water repellency of the copolymer  
15 is increased which lowers the permeability to the liquid. When the amount of the ethylenically unsaturated monomer from (B) or (C) is less than the amounts set out above, the strength of the copolymer is insufficient when it is wet with the body fluid.

20 The water-dispersible copolymers of the present invention may be used as is, or may be partially neutralized to further control the solubility/dispersibility of the copolymer in water. When the degree of neutralization exceeds 50 molar%, however, the water-dispersible

copolymer may be soluble even in water containing 0.5% of a salt. The method for the neutralization is not particularly limited. The polymerization can be followed by the neutralization or, alternatively, the monomer can be neutralized prior to the polymerization. The degree of neutralization of the water-dispersible copolymer is preferably not higher than 50 molar%, more preferably not higher than 40 molar%, and most preferably from about 5% to about 35 molar%. Examples of the alkalis which may be used for the neutralization include NaOH, KOH, LiOH, inorganic salts such as  $\text{Na}_2\text{CO}_3$ ; and amines such as monoethanolamine, diethanolamine, triethanolamine, diethylaminoethanol, ammonia, trimethylamine and morpholine. Preferred alkalis for neutralization are NaOH, KOH, ammonia, ethanolamines, and combinations of an ethanolamine with NaOH or KOH.

The weight average molecular weight of the water-dispersible copolymers of the present invention is greater than about 25,000, preferably from about 25,000 to about 2,000,000, more preferably from about 25,000 to about 1,500,000, and most preferably from about 25,000 to about 1,250,000. When a polymerization terminator is used, the weight average molecular weight of the water-dispersible copolymers of the present invention may be lower, for example, greater than about 25,000, preferably from about 25,000 to about 2,000,000, more preferably from about 25,000 to about 1,500,000, and most preferably from about 25,000 to about 1,250,000. The acidic ethylenically unsaturated monomers from (A), the

ethylenically unsaturated monomers from (B), and the ethylenically unsaturated monomers from (C) are present in any order.

As set out above, to further improve water dispersability, a chain  
5 transfer agent, or polymerization terminator, such as dodecyl mercaptan, may be added to reduce the molecular weight of the water-dispersible copolymer during the polymerization process. On the other hand, crosslinking agents may be employed to increase the molecular weight of the water-dispersible copolymer during the polymerization such as diallyl  
10 phthalate, diallyl amine, allyl methacrylate, ethylene glycol diacrylate, 1,6-hexane diacrylate, methylene, bisacrylamide, divinyl benzene, triallyl amine, triallyl cyanurate, and trimethylolpropane triacrylate.

The precise formulation of the water-dispersible copolymers of the  
15 present invention will vary depending upon the specific end use. Other ingredients may also be incorporated into the copolymer composition as dictated by the nature of the desired composition as well known by those having ordinary skill in the art. Examples of additives traditionally used include plasticizers, tackifiers, thickeners, fillers, humectants, and surfactants which  
20 may be employed in conventional amounts.

Illustrative examples of plasticizers include acetyl tributyl citrate, butyl benzyl phthalate, butyl phthalyl butyl glycolate, dibutyl phthalate,

dibutyl sebacate, diethyl phthalate, diethylene glycol dibenzoate, dipropylene glycol, dipropylene glycol dibenzoate, ethyl phthalyl ethyl glycolate, ethyl-p-toluene sulfonamide, hexylene glycol, methyl phthalyl ethyl glycolate, polyoxyethylene aryl ether, tributoxyethyl phthalate, triethylene glycol polyester of benzoic acid and phthalic acid. Of these plasticizers, 5 dibenzoate types, phthalates, liquid polyesters or sulfonated types are preferred. When present, plasticizers are generally used in amounts of 2 to 20 parts by weight, preferably 3 to 15 parts.

10 Illustrative examples of tackifiers include coumarone-indene, ester gum, gum rosin, hydrocarbon resins, hydrogenated rosin, phenolic modified hydrocarbon resins, rosin esters, tall oil rosins, terpene phenolic, terpene resins, toluene-sulfonamide-formaldehyde resin, and wood rosin. When present, tackifiers are generally used in dispersion form at 40% to 65% 15 solids in amounts up to about 50 parts by weight, preferably 2 to 20 parts.

Illustrative examples of thickeners include associative thickeners such as hydrophobically modified ethoxylated polyurethanes and hydrophobically modified alkali soluble emulsions, as well as alkali soluble 20 emulsions. Other thickeners include oliginates, bentonite, casein, fumed silica, guar gum, gum tragacanth, hydroxy-ethylcellulose, locust bean gum, methylcellulose, polyacrylic acid salts (ammonium, potassium, sodium), polyvinyl alcohol, sodium carboxymethyl cellulose, and starches. When

present, thickeners will be used in amounts up to about 25 parts by weight.

Illustrative examples of fillers include bentonites, calcium carbonate, calcium silicate, clay, mica, nut shell flours, silica, talc, uncooked starches, and wood flour. When present, fillers will be used in amounts up to about 20 parts by weight.

Illustrative examples of humectants include calcium chloride, diethylene glycol, glycerine, hexylene glycol, propylene glycol, magnesium chloride, sodium nitrate, sorbitol, sucrose, and urea. When present, humectants will be used in amounts up to about 20 parts by weight.

Surfactants are often employed in adhesive compositions to increase the penetrating effects of the adhesive. The surfactants may be one or more of anionic, cationic, amphoteric or nonionic surface-active compounds. Suitable anionic emulsifiers are, for example, alkyl sulfonates, alkylaryl sulfonates, alkyl sulfates, sulfates of hydroxyalkanols, alkyl and alkylaryl disulfonates, sulfonated fatty acids, sulfates and phosphates of polyethoxylated alkanols and alkylphenols, as well as esters of sulfosuccinic acid. Suitable cationic emulsifiers are, for example, alkyl quaternary ammonium salts, and alkyl quaternary phosphonium salts. One type of suitable non-ionic emulsifier is the addition product of 5 to 50 moles of ethylene oxide adducted to straight-chain and branched-chain alkanols

with 6 to 22 carbon atoms, or to alkylphenols. higher fatty acids, higher fatty acid amines, or primary and secondary higher alkyl amines. Other suitable non-ionic emulsifiers are one or more block copolymers of propylene oxide with ethylene oxide. Preferred surfactants include fluorinated alkyl  
5 amphoterics or sodium dioctylsulfosuccinate. When present, the surfactant will be used in amounts of about 0.05 to 5.0 parts by weight.

The present invention is also directed to methods for preparing the water-dispersible copolymers in the above embodiments. The water-  
10 dispersible copolymers may be prepared by emulsion polymerization in water at a solids level from about 20% to about 70% in the presence of a surfactant or without a surfactant. No organic solvent is necessary. When the water-dispersible copolymer is polymerized without a surfactant, the monomers are first neutralized in water to a level from about 2% to about  
15 15% molar of the acidic ethylenically unsaturated monomer from (A) to solubilize/disperse the monomers.

A polymerization initiator may be employed in the emulsion polymerization. Examples of the polymerization initiators include ammonium  
20 persulfate, sodium persulfate, hydrogen peroxide, t-butyl hydroperoxide, ascorbic acid, sodium formaldehyde sulfoxylate, sodium meta-bisulfite, dialkyl peroxides, peroxyesters, 2,2'-azobisisobutyronitrile, 2,2'-azobis(2methylbutyronitrile), 2,2'-azobis(2,4-dimethylvaleronitrile), 2,2'-



azobis(2-amidinopropane) dihydrochloride, and 2,2'-azobis(N,N-dimethyleneisobutylamidine). The amount of the polymerization initiator ranges from about 0.01% to about 5% by weight based on the monomers. The polymerization temperature which varies depending on the selection of  
5 monomers ranges from about 30°C. to about 90°C. and the polymerization time ranges from about 1 to about 7 hours.

In a specific embodiment, the present invention is directed to a method for preparing an aqueous emulsion comprising a water-dispersible  
10 copolymer which is non-dispersible in aqueous solutions containing 0.5% or more of an inorganic salt, comprising the steps of:

(a) providing the following monomers in percentages by weight;

(A) from about 10% to about 90% of an acidic ethylenically unsaturated monomer; and

15 (B) from about 10% to about 90% of an ethylenically unsaturated monomer selected from the group of monomer formulas consisting of:

(i)  $\text{CH}_2=\text{C}(\text{R}_1)\text{COR}_2$ ;

(ii)  $\text{R}_3\text{OOC}-\text{CH}=\text{CH}-\text{COOR}_4$ ;

(iii)  $\text{CH}_2=\text{C}(\text{R}_5)\text{OCOR}_6$ ;

20 (iv)  $\text{CH}_2=\text{C}(\text{COOR}_7)\text{CH}_2\text{COOR}_8$ ;

(v)  $\text{CH}_3\text{CH}=\text{CHCOOR}_9$ ;

(vi)  $\text{R}_{10}\text{C}_6\text{H}_4\text{CR}_{11}=\text{CHR}_{11}$ ; and

(vii)  $R_{12}CH=CHR_{13}$ ;

wherein  $R_1$  is hydrogen or methyl and  $R_2$  is  $-OZ'$  or  $-N(Z'')(Z''')$ , wherein  $Z'$  is an alkyl group having from 1 to 7 carbon atoms, and  $Z''$  is independently selected from the group consisting of hydrogen and alkyl groups having from 1 to 6 carbon atoms;  $R_3$  and  $R_4$  are independently hydrogen or an alkyl group having from 1 to 7 carbon atoms, with the proviso that  $R_3$  and  $R_4$  are not both hydrogen;  $R_5$  is hydrogen or methyl and  $R_6$  is an alkyl group having from 1 to 7 carbon atoms;  $R_7$  and  $R_8$  are independently hydrogen or an alkyl group having from 1 to 7 carbon atoms, with the proviso that  $R_7$  and  $R_8$  are not both hydrogen;  $R_9$  is an alkyl group having from 1 to 7 carbon atoms;  $R_{10}$  and  $R_{11}$  are hydrogen;  $R_{12}$  and  $R_{13}$  are independently selected from the group consisting of hydrogen,  $-CN$ ,  $-NHCHO$ ,  $-NHCOCH_3$ , and an alkyl group having from 1 to 7 carbon atoms; and the copolymer has a weight average molecular weight greater than about 25,000 and is present in an amount from about 20% to about 70%; and




(b) emulsion polymerizing the monomers from (A) and (B) in water at a solids level from about 20% to about 70% in the presence of a surfactant.

In another specific embodiment, the present invention is directed to a method for preparing an aqueous emulsion comprising a water-dispersible copolymer which is non-dispersible in aqueous solutions containing 0.5% or more of an inorganic salt, comprising the steps of:

(a) providing the following monomers in percentages by weight;

(A) from about 10% to about 90% of an acidic ethylenically unsaturated monomer; and

(B) from about 10% to about 90% of an ethylenically unsaturated monomer selected from the group of monomer formulas consisting of:



wherein  $\text{R}_1$  is hydrogen or methyl and  $\text{R}_2$  is  $-\text{OZ}'$  or  $-\text{N}(\text{Z}'')(\text{Z}'')$ , wherein  $\text{Z}'$  is an alkyl group having from 1 to 7 carbon atoms, and  $\text{Z}''$  is independently selected from the group consisting of hydrogen and alkyl groups having from 1 to 6 carbon atoms;  $\text{R}_3$  and  $\text{R}_4$  are independently hydrogen or an alkyl group having from 1 to 7 carbon atoms, with the proviso that  $\text{R}_3$  and  $\text{R}_4$  are not both hydrogen;  $\text{R}_5$  is hydrogen or methyl and  $\text{R}_6$  is an alkyl group having from 1 to 7 carbon atoms;  $\text{R}_7$  and  $\text{R}_8$  are independently hydrogen or an alkyl group having from 1 to 7 carbon atoms, with the proviso that  $\text{R}_7$  and  $\text{R}_8$  are not both hydrogen;  $\text{R}_9$  is an alkyl group having from 1 to 7 carbon atoms;  $\text{R}_{10}$  and  $\text{R}_{11}$  are hydrogen;  $\text{R}_{12}$  and  $\text{R}_{13}$  are independently selected from the group consisting of hydrogen,  $-\text{CN}$ ,  $-\text{NHCHO}$ ,  $-\text{NHCOCH}_3$ , and an alkyl

group having from 1 to 7 carbon atoms; and the copolymer has a weight average molecular weight greater than about 25,000 and is present in an amount from about 20% to about 70%; and

(b) neutralizing the monomers from (A) and (B) in water to a level  
5 from about 2% to about 15% molar of the acidic ethylenically unsaturated monomer from (A); and


(c) emulsion polymerizing the monomers from (A) and (B) at a solids level from about 20% to about 70% without a surfactant.

10 In another specific embodiment, the present invention is directed to a method for preparing an aqueous emulsion comprising a water-dispersible copolymer which is non-dispersible in aqueous solutions containing 0.5% or more of an inorganic salt, comprising the steps of:

(a) providing the following monomers in percentages by weight;

15 (A) from about 10% to about 90% of an acidic ethylenically unsaturated monomer; and

(B) from about 10% to about 90% of an ethylenically unsaturated monomer selected from the group of monomer formulas consisting of:



(v)  $\text{CH}_3\text{CH}=\text{CHCOOR}'_9$ ;

(vi)  $\text{R}'_{10}\text{C}_6\text{H}_4\text{CR}'_{11}=\text{CHR}'_{11}$ ; and

(vii)  $\text{R}'_{12}\text{CH}=\text{CHR}'_{13}$ ;

wherein  $\text{R}'_1$  is hydrogen or methyl, and  $\text{R}'_2$  is selected from the group  
 5 consisting of  $-\text{OZ}'$ ,  $-\text{N}(\text{Z}'')(\text{Z}''')$ , and  $-\text{OZ}'''\text{OH}$ , wherein  $\text{Z}'$  is an alkyl group  
 having from 8 to 18 carbon atoms;  $\text{Z}''$  is independently selected from the  
 group consisting of alkyl groups having from 7 to 10 carbon atoms,  
 dimethylamino alkyl groups having from 1 to 5 carbon atoms, and  
 hydroxyalkyl groups having from 1 to 5 carbon atoms; and  $\text{Z}'''$  is an alkyl  
 10 group having from 1 to 4 carbon atoms;  $\text{R}'_3$  and  $\text{R}'_4$  are independently an  
 alkyl group having from 8 to 18 carbon atoms;  $\text{R}'_5$  is hydrogen or methyl and  
 $\text{R}'_6$  is an alkyl group having from 8 to 18 carbon atoms;  $\text{R}'_7$  and  $\text{R}'_8$  are  
 independently an alkyl group having from 8 to 18 carbon atoms;  $\text{R}'_9$  is an  
 alkyl group having from 8 to 18 carbon atoms;  $\text{R}'_{10}$  and  $\text{R}'_{11}$  are  
 15 independently an alkyl group having from 1 to 2 carbon atoms;  $\text{R}'_{12}$  and  $\text{R}'_{13}$   
 are independently selected from the group consisting of 2-pyrrolidinone, N-  
 caprolactam, 2-pyridine, 3-pyridine, 4-pyridine, and an alkyl group having  
 from 7 to 18 carbon atoms, with the proviso that  $\text{R}_{12}$  and  $\text{R}_{13}$  are not at the  
 same time 2-pyrrolidinone, N-caprolactam, 2-pyridine, 3-pyridine, or 4-  
 20 pyridine; and the copolymer has a weight average molecular weight greater  
 than about 25,000 and is present in an amount from about 20% to about  
 70%; and

(b) emulsion polymerizing the monomers from (A) and (B) in water at a solids level from about 20% to about 70% in the presence of a surfactant.

5 In another specific embodiment, the present invention is directed to a method for preparing an aqueous emulsion comprising a water-dispersible copolymer which is non-dispersible in aqueous solutions containing 0.5% or more of an inorganic salt, comprising the steps of:

(a) providing the following monomers in percentages by weight;

10 (A) from about 10% to about 90% of an acidic ethylenically unsaturated monomer; and

(B) from about 10% to about 90% of an ethylenically unsaturated monomer selected from the group of monomer formulas consisting of:

(i)  $\text{CH}_2=\text{C}(\text{R}'_1)\text{COR}'_2$ ;

15 (ii)  $\text{R}'_3\text{OOC}-\text{CH}=\text{CH}-\text{COOR}'_4$ ;

(iii)  $\text{CH}_2=\text{C}(\text{R}'_5)\text{OCOR}'_6$ ;

(iv)  $\text{CH}_2=\text{C}(\text{COOR}'_7)\text{CH}_2\text{COOR}'_8$ ;

(v)  $\text{CH}_3\text{CH}=\text{CHCOOR}'_9$ ;

(vi)  $\text{R}'_{10}\text{C}_6\text{H}_4\text{CR}'_{11}=\text{CHR}'_{11}$ ; and

20 (vii)  $\text{R}'_{12}\text{CH}=\text{CHR}'_{13}$ ;

wherein  $\text{R}'_1$  is hydrogen or methyl, and  $\text{R}'_2$  is selected from the group consisting of  $-\text{OZ}'$ ,  $-\text{N}(\text{Z}'')(\text{Z}'')$ , and  $-\text{OZ}'''\text{OH}$ , wherein  $\text{Z}'$  is an alkyl group having from 8 to 18 carbon atoms;  $\text{Z}''$  is independently selected from the

group consisting of alkyl groups having from 7 to 10 carbon atoms, dimethylamino alkyl groups having from 1 to 5 carbon atoms, and hydroxyalkyl groups having from 1 to 5 carbon atoms; and Z''' is an alkyl group having from 1 to 4 carbon atoms; R'<sub>3</sub> and R'<sub>4</sub> are independently an alkyl group having from 8 to 18 carbon atoms; R'<sub>5</sub> is hydrogen or methyl and R'<sub>6</sub> is an alkyl group having from 8 to 18 carbon atoms; R'<sub>7</sub> and R'<sub>8</sub> are independently an alkyl group having from 8 to 18 carbon atoms; R'<sub>9</sub> is an alkyl group having from 8 to 18 carbon atoms; R'<sub>10</sub> and R'<sub>11</sub> are independently an alkyl group having from 1 to 2 carbon atoms; R'<sub>12</sub> and R'<sub>13</sub> are independently selected from the group consisting of 2-pyrrolidinone, N-caprolactam, 2-pyridine, 3-pyridine, 4-pyridine, and an alkyl group having from 7 to 18 carbon atoms, with the proviso that R'<sub>12</sub> and R'<sub>13</sub> are not at the same time 2-pyrrolidinone, N-caprolactam, 2-pyridine, 3-pyridine, or 4-pyridine; and the copolymer has a weight average molecular weight greater than about 25,000 and is present in an amount from about 20% to about 70%; and

(b) neutralizing the monomers from (A) and (B) in water to a level from about 2% to about 15% molar of the acidic ethylenically unsaturated monomer from (A); and

(c) emulsion polymerizing the monomers from (A) and (B) at a solids level from about 20% to about 70% without a surfactant.

In another specific embodiment, the present invention is directed to a method for preparing an aqueous emulsion comprising a water-dispersible copolymer which is non-dispersible in aqueous solutions containing 0.5% or more of an inorganic salt, comprising the steps of:

5 (a) providing the following monomers in percentages by weight;

(A) from about 10% to about 80% of an acidic ethylenically unsaturated monomer;

(B) from about 10% to about 80% of an ethylenically unsaturated monomer selected from the group of monomer formulas consisting of:

- 10 (i)  $\text{CH}_2=\text{C}(\text{R}_1)\text{COR}_2$ ;  
(ii)  $\text{R}_3\text{OOC}-\text{CH}=\text{CH}-\text{COOR}_4$ ;  
(iii)  $\text{CH}_2=\text{C}(\text{R}_5)\text{OCOR}_6$ ;  
(iv)  $\text{CH}_2=\text{C}(\text{COOR}_7)\text{CH}_2\text{COOR}_8$ ;  
(v)  $\text{CH}_3\text{CH}=\text{CHCOOR}_9$ ;  
15 (vi)  $\text{R}_{10}\text{C}_6\text{H}_4\text{CR}_{11}=\text{CHR}_{11}$ ; and  
(vii)  $\text{R}_{12}\text{CH}=\text{CHR}_{13}$ ;

wherein  $\text{R}_1$  is hydrogen or methyl and  $\text{R}_2$  is  $-\text{OZ}'$  or  $-\text{N}(\text{Z}'')(\text{Z}''')$ , wherein  $\text{Z}'$  is an alkyl group having from 1 to 7 carbon atoms, and  $\text{Z}''$  is independently selected from the group consisting of hydrogen and alkyl groups having from  
20 1 to 6 carbon atoms;  $\text{R}_3$  and  $\text{R}_4$  are independently hydrogen or an alkyl group having from 1 to 7 carbon atoms, with the proviso that  $\text{R}_3$  and  $\text{R}_4$  are not both hydrogen;  $\text{R}_5$  is hydrogen or methyl and  $\text{R}_6$  is an alkyl group having from 1 to 7 carbon atoms;  $\text{R}_7$  and  $\text{R}_8$  are independently hydrogen or an alkyl



group having from 1 to 7 carbon atoms, with the proviso that  $R_7$  and  $R_8$  are not both hydrogen;  $R_9$  is an alkyl group having from 1 to 7 carbon atoms;  $R_{10}$  and  $R_{11}$  are hydrogen; and  $R_{12}$  and  $R_{13}$  are independently selected from the group consisting of hydrogen, -CN, -NHCHO, and an alkyl group having from 1 to 7 carbon atoms; and

(C) from about 10% to about 80% of an ethylenically unsaturated monomer selected from the group of monomer formulas consisting of:

- (i)  $\text{CH}_2=\text{C}(\text{R}'_1)\text{COR}'_2$ ;
- (ii)  $\text{R}'_3\text{OOC}-\text{CH}=\text{CH}-\text{COOR}'_4$ ;
- (iii)  $\text{CH}_2=\text{C}(\text{R}'_5)\text{OCOR}'_6$ ;
- (iv)  $\text{CH}_2=\text{C}(\text{COOR}'_7)\text{CH}_2\text{COOR}'_8$ ;
- (v)  $\text{CH}_3\text{CH}=\text{CHCOOR}'_9$ ;
- (vi)  $\text{R}'_{10}\text{C}_6\text{H}_4\text{CR}'_{11}=\text{CHR}'_{11}$ ; and
- (vii)  $\text{R}'_{12}\text{CH}=\text{CHR}'_{13}$ ;

wherein  $\text{R}'_1$  is hydrogen or methyl, and  $\text{R}'_2$  is selected from the group consisting of -OZ', -N(Z'')(Z''), and -OZ'''OH, wherein Z' is an alkyl group having from 8 to 18 carbon atoms; Z'' is independently selected from the group consisting of alkyl groups having from 7 to 10 carbon atoms, dimethylamino alkyl groups having from 1 to 5 carbon atoms, and hydroxyalkyl groups having from 1 to 5 carbon atoms; and Z''' is an alkyl group having from 1 to 4 carbon atoms;  $\text{R}'_3$  and  $\text{R}'_4$  are independently an alkyl group having from 8 to 18 carbon atoms;  $\text{R}'_5$  is hydrogen or methyl and  $\text{R}'_6$  is an alkyl group having from 8 to 18 carbon atoms;  $\text{R}'_7$  and  $\text{R}'_8$  are

independently an alkyl group having from 8 to 18 carbon atoms; R'<sub>9</sub> is an alkyl group having from 8 to 18 carbon atoms; R'<sub>10</sub> and R'<sub>11</sub> are independently an alkyl group having from 1 to 2 carbon atoms; R'<sub>12</sub> and R'<sub>13</sub> are independently selected from the group consisting of 2-pyrrolidinone, N-caprolactam, and an alkyl group having from 7 to 18 carbon atoms, with the proviso that R<sub>12</sub> and R<sub>13</sub> are not both 2-pyrrolidinone, are not both N-caprolactam, or are not a mixture thereof; and the copolymer has a weight average molecular weight greater than about 25,000 and is present in an amount from about 20% to about 70%; and

(b) emulsion polymerizing the monomers from (A), (B), and (C) in water at a solids level from about 20% to about 70% in the presence of a surfactant.

In another specific embodiment, the present invention is directed to a method for preparing an aqueous emulsion comprising a water-dispersible copolymer which is non-dispersible in aqueous solutions containing 0.5% or more of an inorganic salt, comprising the steps of:

(a) providing the following monomers in percentages by weight;

(A) from about 10% to about 80% of an acidic ethylenically unsaturated monomer;



(B) from about 10% to about 80% of an ethylenically unsaturated monomer selected from the group of monomer formulas consisting of:

- (i)  $\text{CH}_2=\text{C}(\text{R}_1)\text{COR}_2$ ;
- (ii)  $\text{R}_3\text{OOC}-\text{CH}=\text{CH}-\text{COOR}_4$ ;
- (iii)  $\text{CH}_2=\text{C}(\text{R}_5)\text{OCOR}_6$ ;
- (iv)  $\text{CH}_2=\text{C}(\text{COOR}_7)\text{CH}_2\text{COOR}_8$ ;
- 5 (v)  $\text{CH}_3\text{CH}=\text{CHCOOR}_9$ ;
- (vi)  $\text{R}_{10}\text{C}_6\text{H}_4\text{CR}_{11}=\text{CHR}_{11}$ ; and
- (vii)  $\text{R}_{12}\text{CH}=\text{CHR}_{13}$ ;

wherein  $\text{R}_1$  is hydrogen or methyl and  $\text{R}_2$  is  $-\text{OZ}'$  or  $-\text{N}(\text{Z}'')(\text{Z}'')$ , wherein  $\text{Z}'$  is an alkyl group having from 1 to 7 carbon atoms, and  $\text{Z}''$  is independently  
 10 selected from the group consisting of hydrogen and alkyl groups having from 1 to 6 carbon atoms;  $\text{R}_3$  and  $\text{R}_4$  are independently hydrogen or an alkyl group having from 1 to 7 carbon atoms, with the proviso that  $\text{R}_3$  and  $\text{R}_4$  are not both hydrogen;  $\text{R}_5$  is hydrogen or methyl and  $\text{R}_6$  is an alkyl group having from 1 to 7 carbon atoms;  $\text{R}_7$  and  $\text{R}_8$  are independently hydrogen or an alkyl  
 15 group having from 1 to 7 carbon atoms, with the proviso that  $\text{R}_7$  and  $\text{R}_8$  are not both hydrogen;  $\text{R}_9$  is an alkyl group having from 1 to 7 carbon atoms;  $\text{R}_{10}$  and  $\text{R}_{11}$  are hydrogen; and  $\text{R}_{12}$  and  $\text{R}_{13}$  are independently selected from the group consisting of hydrogen,  $-\text{CN}$ ,  $-\text{NHCHO}$ , and an alkyl group having from 1 to 7 carbon atoms; and

20 (C) from about 10% to about 80% of an ethylenically unsaturated monomer selected from the group of monomer formulas consisting of:

- (i)  $\text{CH}_2=\text{C}(\text{R}'_1)\text{COR}'_2$ ;



wherein  $R'_1$  is hydrogen or methyl, and  $R'_2$  is selected from the group consisting of  $-OZ'$ ,  $-N(Z'')(Z'')$ , and  $-OZ'''OH$ , wherein  $Z'$  is an alkyl group having from 8 to 18 carbon atoms;  $Z''$  is independently selected from the

10 group consisting of alkyl groups having from 7 to 10 carbon atoms, dimethylamino alkyl groups having from 1 to 5 carbon atoms, and hydroxyalkyl groups having from 1 to 5 carbon atoms; and  $Z'''$  is an alkyl group having from 1 to 4 carbon atoms;  $R'_3$  and  $R'_4$  are independently an alkyl group having from 8 to 18 carbon atoms;  $R'_5$  is hydrogen or methyl and

15  $R'_6$  is an alkyl group having from 8 to 18 carbon atoms;  $R'_7$  and  $R'_8$  are independently an alkyl group having from 8 to 18 carbon atoms;  $R'_9$  is an alkyl group having from 8 to 18 carbon atoms;  $R'_{10}$  and  $R'_{11}$  are independently an alkyl group having from 1 to 2 carbon atoms;  $R'_{12}$  and  $R'_{13}$  are independently selected from the group consisting of 2-pyrrolidinone, N-caprolactam, and an alkyl group having from 7 to 18 carbon atoms, with the

20 proviso that  $R'_{12}$  and  $R'_{13}$  are not both 2-pyrrolidinone, are not both N-caprolactam, or are not a mixture thereof; and the copolymer has a weight average molecular weight greater than about 25,000 and is present in an

amount from about 20% to about 70%; and

(b) neutralizing the monomers from (A), (B), and (C) in water to a level from about 2% to about 15% molar of the acidic ethylenically unsaturated monomer from (A); and

5 (c) emulsion polymerizing the monomers from (A), (B), and (C) at a solids level from about 20% to about 70% without a surfactant.

Throughout this application, various publications have been referenced. The disclosures in these publications are incorporated herein by  
10 reference in order to more fully describe the state of the art.

Throughout this disclosure, applicant will suggest various theories or mechanisms by which applicant believes the components in the adhesive compositions function together in an unexpected manner to provide unique  
15 waterborne hot melt agents. While applicant may offer various mechanisms to explain the present invention, applicant does not wish to be bound by theory. These theories are suggested to better understand the present invention but are not intended to limit the effective scope of the claims.

20 The present invention is further illustrated by the following examples which are presented for purposes of demonstrating, but not limiting, the preparation of the compounds and compositions of this invention.

## Examples

### Example 1 (Surfactant process)

5

A quantity of 382.0 grams of deionized water and 5.7 grams Abex EP-120 were added to a 2-L four-neck flask equipped with a condenser, thermometer and stainless steel paddle agitator. The pH was adjusted to 2.5 with sulfuric acid, and the solution was stirred and purged with a gentle stream of nitrogen for 30 minutes. Next, a solution of 10 grams deionized water and 1.0 gram ammonium persulfate was added. Then 100.0 grams of deionized water and 11.4 grams Abex EP-120 were mixed and to that solution were added 120.0 grams methacrylic acid, 50.0 grams butyl acrylate, 30.0 grams 2-ethylhexyl acrylate, and 0.6 grams dodecyl mercaptan. The reaction mixture was heated to 80°C with a water bath, and at 80°C, the monomer preemulsion was added over 2.5 hours via monomer pump, and the reaction was held at 80°C for 30 minutes after all of the monomer was added. The resulting emulsion was 29.7% solids with a pH of 2.2, a viscosity of 85 cPs, and an average particle size of 82 nm. The polymer was soluble in alkali, and dried films dispersed in tap water, but were insoluble in 3% salt solutions.

20

## Example 2

The polymerization was conducted in the same manner as Example 1 except that 50 grams of butyl acrylate and 50 grams methacrylic acid were used as the monomers. The resulting emulsion was 28.3% solids with a pH of 2.2, a viscosity of 10 cPs, and an average particle size of 78 nm. The polymer was soluble in alkali, and dried films dispersed in tap water, but were insoluble in 3% salt solutions.

## Example 3

The polymerization was conducted in the same manner as Example 1 except that 50 grams of 2-ethylhexyl acrylate and 50 grams methacrylic acid were used as the monomers. The resulting emulsion was 27.3% solids with a pH of 2.1, a viscosity of 26 cPs, and an average particle size of 102 nm. The polymer was soluble in alkali, and dried films dispersed in tap water but were insoluble in 3% salt solutions

## Example 4

20

The polymerization was conducted in the same manner as Example 1 except that 50 grams methacrylic acid, 30 grams butyl acrylate, 20 grams 2-ethylhexyl acrylate, and 10 grams maleic anhydride were used as the

monomers. The resulting emulsion was 27.6% solids with a pH of 1.4, and a viscosity of 36 cPs. the polymer was soluble in alkali, and dried films dispersed in tap water, but were insoluble in 3% salt solutions.

5      Example 5

The polymerization was conducted in the same manner as Example 1 except that 50 grams methacrylic acid, 30 grams butyl acrylate, 20 grams 2-ethylhexyl acrylate, and 10 grams vinyl acetate were used as the monomers. The resulting emulsion was 30.3% solids with a pH of 2.1, and a viscosity of 12 cPs. The polymer was soluble in alkali, and dried films dispersed in tap water, but were insoluble in 3% salt solutions.

Example 6

15

The polymerization was conducted in the same manner as Example 1 except that 50 grams methacrylic acid, 30 grams butyl acrylate, 20 grams 2-ethylhexyl acrylate, and 10 grams mono-octyl maleate were used as the monomers. The resulting emulsion was 30.0% solids with a pH of 1.6, and a viscosity of 12 cPs. The polymer was soluble in alkali, and dried films dispersed in tap water, but were insoluble in 3% salt solutions.

20



## Example 7

The polymerization was conducted in the same manner as Example 1 except that 50 grams methacrylic acid, 30 grams butyl acrylate, 20 grams 2-ethylhexyl acrylate, and 10 grams itaconic acid were used as the monomers. The resulting emulsion was 25.6% solids with a pH of 2.1, and a viscosity of 12 cPs. The polymer was soluble in alkali, and dried films dispersed in tap water, but were insoluble in 3% salt solutions.

## 10 Example 8

The polymerization was conducted in the same manner as Example 1 except that 50 grams methacrylic acid, 30 grams butyl acrylate, 20 grams 2-ethylhexyl acrylate, and 5 grams 2-acrylamido-2-methylpropane sulfonic acid were used as the monomers. The resulting emulsion was 25.6% solids with a pH of 2.1, and a viscosity of 12 cPs. The polymer was soluble in alkali, and dried films dispersed in tap water, but were insoluble in 3% salt solutions.

## Example 9

A quantity of 388.5 grams of deionized water, 3.0 grams Aerosol A-102 and 3.0 grams Rhodasurf L-4 were added to a 2-L four-neck flask equipped with a condenser, thermometer and stainless steel paddle agitator. The solution was stirred and purged with a gentle stream of nitrogen for 30 minutes. Next, 300.0 grams of deionized water, 3.0 grams Rhodasurf L-4, and 3.0 grams Aerosol A-102 were mixed and to that solution were added 162.0 grams methacrylic acid, 8.0 grams acrylic acid, 75.0 grams butyl acrylate, 15.0 grams methyl methacrylate, and 0.3 grams dodecyl mercaptan. Then 30.0 grams of this monomer emulsion was added to the initial charge, and the mixture was heated to 80°C with a water bath. At 76°C, a solution of 15 grams deionized water and 1.5 grams ammonium persulfate was added. The reaction mixture was allowed to react for 5 minutes, then the monomer pre-emulsion was added over 2.5 hours via monomer pump, and the reaction was held at 80°C for 15 minutes after all of the monomer was added. The resulting emulsion was 29.5 solids with a pH of 2.1 a viscosity of 13.5 cPs and an average particle size of 117 nm. The polymer was soluble in alkali, and dried films dispersed in tap water, but were insoluble in 3% salt solutions.

## Example 10

Films from above examples were cast and air dried. Next, 1.0 gram was placed in a flask with 100.0 grams tap water. The solution was stirred for 1 hour, then filtered and the % solids was determined on the filtrate to calculate the % insoluble polymer. The results are tabulated below:

## Salt Sensitivity of Selected Latexes.

	% Insoluble in Tap Water	% Insoluble in 3% NaCl
Example 1	15.9%	96.7%
Example 2	0.0%	100%
Example 3	46.2%	100%
Example 5	10.2%	100%
Example 7	8.2%	100%
Example 8	7.4%	92.0%
Example 9	5.7%	95.1%

Example 11 (In-situ colloid process, no surfactant)

A quantity of 675.0 grams deionized water and 4.89 grams ammonium hydroxide were added to a 2-L four-neck flask equipped with a condenser, thermometer and stainless steel paddle agitator. The solution was stirred and purged with a gentle stream of nitrogen for 30 minutes. Next, 6.0 grams of acrylic acid and 0.6 grams of dodecyl mercaptan were added, and the mixture was heated to 80°C with a water bath. At 75°C, a solution of 15.0 grams deionized water and 1.5 grams ammonium persulfate was added and the reaction was allowed to heat to 80°C. At 80°C, a quantity of 180.0 grams methacrylic acid, 75.0 grams butyl acrylate, and 45.0 grams 2-ethylhexyl acrylate, were added over 2.5 hours via monomer pump. The resulting emulsion was 29.7% solids with a pH of 4.0, and a viscosity of 136 cPs.

15

Example 12

The polymerization was conducted in the same manner as Example 10 except the monomer slow addition composition was 30 grams methacrylic acid, 40 grams butyl acrylate, and 30 grams 2-ethylhexyl acrylate. The resulting emulsion was 29.6% solids with a pH of 4.6, and a viscosity of 14 cPs. The polymer was soluble in alkali, and dried films dispersed in tap water, but were insoluble in 3% salt solutions. The polymer

20

was also a film former at room temperature.

#### Example 13

5           The polymerization was conducted in the same manner as Example  
10 except the monomer slow addition composition was 30 grams  
methacrylic acid and 70 grams butyl acrylate. The resulting emulsion was  
29.5% solids with a pH of 4.4, and a viscosity of 348 cPs. The polymer was  
soluble in alkali, and dried films dispersed in tap water, but were insoluble in  
10 3% salt solutions. The polymer was also a film former at room temperature.

#### Example 14

          The polymerization was conducted in the same manner as Example  
15 10 except the monomer slow addition composition was 30 grams  
methacrylic acid, and 70 grams 2-ethylhexyl acrylate. The resulting  
emulsion was 29.6% solids with a pH of 4.4, and a viscosity of 210 cPs.  
The polymer was soluble in alkali, and dried films dispersed in tap water, but  
were insoluble in 3% salt solutions. The polymer was also a film former at  
20 room temperature.

## Example 15

The polymerization was conducted in the same manner as Example 10 except the monomer slow addition composition was 60 grams methacrylic acid, 25 grams butyl acrylate, 15 grams 2-ethylhexyl acrylate, and 10 grams maleic anhydride. The resulting emulsion was 29.2% solids with a pH of 1.7, and a viscosity of 12 cPs. The polymer was soluble in alkali, and dried films dispersed in tap water, but were insoluble in 3% salt solutions.

10

## Example 16

The polymerization was conducted in the same manner as Example 10 except the monomer slow addition composition was 60 grams methacrylic acid, 25 grams butyl acrylate, 15 grams 2-ethylhexyl acrylate, and 10 grams vinyl acetate. The resulting emulsion was 29.4% solids with a pH of 2.2, and a viscosity of 10 cPs. The polymer was soluble in alkali, and dried films dispersed in tap water, but were insoluble in 3% salt solutions.

15

20

## Example 17

The polymerization was conducted in the same manner as Example 10 except the monomer slow addition composition was 60 grams

methacrylic acid, 25 grams butyl acrylate, 15 grams 2-ethylhexyl acrylate, and 10 grams monooctyl maleate. The resulting emulsion was 29.7% solids with a pH of 4.0, and a viscosity of 14 cPs. The polymer was soluble in alkali, and dried films dispersed in tap water, but were insoluble in 3% salt solutions.

#### Example 18

The polymerization was conducted in the same manner as Example 10 except the monomer slow addition composition was 40 grams methacrylic acid, 50 grams vinyl acetate, and 10 grams monooctyl maleate. The resulting emulsion was 24.5% solids with a pH of 4.0, and a viscosity of 2140 cPs. The polymer was soluble in alkali, and dried films dispersed in tap water, but were insoluble in 3% salt solutions. The polymer was also a film former at room temperature.

#### Example 19

The polymerization was conducted in the same manner as Example 10 except the monomer slow addition composition was 60 grams acrylic acid, 25 grams butyl acrylate, 15 grams 2ethylhexyl acrylate, and 5 grams 2-acrylamido-2-methylpropane sulfonic acid. The resulting emulsion was 29.8% solids with a pH of 1.8, and a viscosity of 2680 cPs. The polymer

was soluble in alkali, and dried films dispersed in tap water, but were insoluble in 3% salt solutions. The polymer was also a film former at room temperature.

5      Example 20

The polymerization was conducted in the same manner as Example 10 except the monomer slow addition composition was 30 grams acrylic acid, 30 grams methacrylic acid, 25 grams butyl acrylate, and 15 grams 2-ethylhexyl acrylate. The resulting emulsion was 29.7% solids with a pH of 3.5, and a viscosity of 1020 cPs. The polymer was soluble in alkali, and dried films dispersed in tap water, but were insoluble in 3% salt solutions. The polymer was also a film former at room temperature.

15      Example 21

A quantity of 742.0 grams deionized water and 1.0 grams ammonium hydroxide were added to a 2-L four-neck flask equipped with a condenser, thermometer and stainless steel paddle agitator. The solution was stirred and purged with a gentle stream of nitrogen for 30 minutes. Next, 6.0 grams of methacrylic acid and 0.15 grams of dodecyl mercaptan were added, and the mixture was heated to 80°C with a water bath. At 75°C, a solution of 15.0 grams deionized water and 1.5 grams ammonium



persulfate was added and the reaction was allowed to heat to 80°C. At 80°C, a quantity of 172.0 grams methacrylic acid, 80.0 grams butyl acrylate, 15.0 grams monooctyl maleate, 48.0 methyl methacrylate, and 0.15 dodecyl mercaptan were added over 2.5 hours via monomer pump. The resulting  
5 emulsion was 30.1% solids with a pH of 2.8, and a viscosity of 32 cPs.

#### Example 22

The polymerization was conducted in the same manner as Example  
10 21 except the monomer slow addition composition was 60 grams methacrylic acid, 25 grams butyl acrylate, 15 grams methyl methacrylate and 5 grams of the ammonium salt of 2-acrylamido-2-methylpropane sulfonic acid. The resulting latex was 30.0% solids with a pH of 3.5 and a viscosity of 56 cPs. The polymer was soluble in alkali, and dried films dispersed in  
15 tap water but were insoluble in 3% salt solutions.

#### Example 23

Films from the above examples were cast and air-dried. Next, 1.0  
20 gram was placed in a flask with 100.0 grams tap water. The solution was stirred for 1 hour, then filtered and % solids were determined on the filtrate to calculate the % insoluble polymer. The results are tabulated below:

	% Insoluble in	% Insoluble in
	Tap Water	3% NaCl
Example 10	20.9%	81.6%
5 Example 11	21.5%	23.6%
Example 12	16.9%	20.6%
Example 13	9.8%	39.8%
Example 14	19.9%	66.0%
Example 15	15.9%	47.0%
10 Example 20	2.3%	100%

Higher solids latexes can be prepared with conventional techniques, however ultra-high solids using techniques outlined in United states patent no. 6,001,916 can also be utilized. This patent demonstrates  
15 that low viscosity, high solids emulsions (>65%) can be formed by the use of a broad particle size distribution and/or seed emulsions in the initial charge.

Example 24 (high solids)

The polymerization was conducted in the same manner as Example 1 except that 60 grams of methacrylic acid, 15 grams methyl methacrylate, and 25 grams butyl acrylate were used as the monomers. The theoretical solids of this emulsion is 55%.

Example 25

The polymerization was conducted in the same manner as Example 1 except that 60 grams of methacrylic acid, 15 grams methyl methacrylate, and 25 grams butyl acrylate were used as the monomers. These monomers were polymerized in an initial charge which contained a 50% solids polymer made via example 22 instead of water to increase the solids content. The theoretical solids of this emulsion is 65%.

Example 26

Films from several examples of water-dispersible copolymers were cast and air-dried. Next, 1.0 gram was placed in a flask with 100.0 grams tap water. The solution was stirred for 1 hour, then filtered and % solids were determined on the filtrate to calculate the % insoluble polymer. The results are tabulated below:

	Monomer Composition	Surfactant	Substrate	Solubility	
				Tap 3% NaCl	
5	60 MAA/ 25 BA/ 15 2EHA	Yes	Glass, Hair, Wood	Yes	No
	60 MAA/ 25 BA/ 15 2EHA	No	Glass, Hair, Wood	Yes	No
10	50 MAA/ 30 BA/ 20 2EHA	Yes	Glass	Yes	No
	30 MAA/ 40 BA/ 30 2EHA	No	Glass	Yes	No
	60 MAA/ 25 BA/ 15 2EHA/ 5 VA	Yes	Glass	Yes	No
	60 MAA/ 25 BA/ 15 2EHA/ 5 VA	No	Glass	Yes	No
	60 MAA/ 25 BA/ 15 2EHA/ 5 MOM	Yes	Glass	Yes	No
15	60 MAA/ 25 BA/ 15 2EHA/ 5 MOM	No	Glass	Yes	No
	60 MAA/ 25 BA/ 15 2EHA/ 5 MAH	Yes	Glass	Yes	No
	60 MAA/ 25 BA/ 15 2EHA/ 5 MAH	No	Glass	Yes	No
	60 MAA/ 25 BA/ 15 2EHA/ 5 AMPS	Yes	Glass	Yes	No
	60 MAA/ 25 BA/ 15 2EHA/ 5 AMPS	No	Glass	Yes	No
20	50 VA/ 50 MOM	No	Glass	No	No
	40 VA/ 10 MOM/ 30 MAA	No	Glass	Yes	No
	70 MAA/ 20 BA/ 10 2EHA	Yes	Glass	Yes	No
	70 MAA/ 20 BA/ 10 2EHA	No	Glass	Yes	No
	60 MAA/ 25 BA/ 15 MMA	Yes	Glass	Yes	No
	60 MAA/ 25 BA/ 15 MMA	No	Glass	Yes	No
25	60 MAA/25 BA/15 MMA/ 5 AMPS	Yes	Glass	Yes	No
	60 MAA/25 BA/15 MMA/ 5 AMPS	No	Glass	Yes	No
	54 MAA/ 6 AA/ 25 BA/ 15 MMA	Yes	Glass	Yes	No
	54 MAA/ 6 AA/ 25 BA/ 15 MMA	No	Glass	Yes	No
30	54 MAA/ 6 AA/ 25 BA/ 15 MMA/ 5 MOM	Yes	Glass	Yes	No
	54 MAA/ 6 AA/ 25 BA/ 15 MMA/ 5 MOM	No	Glass	Yes	No

In the Table above, the following abbreviations have the meaning set out below.

- AA - acrylic acid
- 5 MAA - methacrylic acid
- MMA - methyl methacrylate
- BA - butyl acrylate
- 2EHA - 2-ethylhexyl acrylate
- AMPS - ammonium salt of 2-acrylamido-2-methylpropane sulfonic acid
- 10 MOM - monooctyl maleate
- VA - vinyl acetate
- MAH - maleic anhydride





While a number of embodiments of this invention have been  
15 represented, it is apparent that the basic construction can be altered to  
provide other embodiments which utilize the invention without departing from  
the spirit and scope of the invention. All such modifications and variations  
are intended to be included within the scope of the invention as defined in  
the appended claims rather than the specific embodiments which have been  
20 presented by way of example.

I claim:

1. An aqueous emulsion comprising a water-dispersible copolymer which is non-dispersible in aqueous solutions containing 0.5% or more of an inorganic salt, wherein the water-dispersible copolymer comprises in percentages by weight:

(A) from about 10% to about 90% of an acidic ethylenically unsaturated monomer; and

(B) from about 10% to about 90% of an ethylenically unsaturated monomer selected from the group of monomer formulas consisting of:



wherein  $\text{R}_1$  is hydrogen or methyl and  $\text{R}_2$  is  $-\text{OZ}'$  or  $-\text{N}(\text{Z}'')(\text{Z}''')$ , wherein  $\text{Z}'$  is an alkyl group having from 1 to 7 carbon atoms, and  $\text{Z}''$  is independently selected from the group consisting of hydrogen and alkyl groups having from 1 to 6 carbon atoms;  $\text{R}_3$  and  $\text{R}_4$  are independently hydrogen or an alkyl group having from 1 to 7 carbon atoms, with the proviso that  $\text{R}_3$  and  $\text{R}_4$  are not both hydrogen;  $\text{R}_5$  is hydrogen or methyl and  $\text{R}_6$  is an alkyl group having

from 1 to 7 carbon atoms; R<sub>7</sub> and R<sub>8</sub> are independently hydrogen or an alkyl group having from 1 to 7 carbon atoms, with the proviso that R<sub>7</sub> and R<sub>8</sub> are not both hydrogen; R<sub>9</sub> is an alkyl group having from 1 to 7 carbon atoms; R<sub>10</sub> and R<sub>11</sub> are hydrogen; R<sub>12</sub> and R<sub>13</sub> are independently selected from the group consisting of hydrogen, -CN, -NHCHO, -NHCOCH<sub>3</sub>, and an alkyl group having from 1 to 7 carbon atoms; and the copolymer has a weight average molecular weight greater than about 25,000 and is present in an amount from about 20% to about 70%.

10           2. The aqueous emulsion according to claim 1, wherein the acidic ethylenically unsaturated monomer from (A) is a carboxylic acid group selected from the group consisting of acrylic acid, methacrylic acid, maleic acid, maleic acid half esters, maleic anhydride, itaconic acid, and crotonic acid.

15           3. The aqueous emulsion according to claim 1, wherein the acidic ethylenically unsaturated monomer from (A) is a sulfonic acid group selected from the group consisting of styrene sulfonic acid, 2-acrylamido-2-methylpropane sulfonic acid, and sodium vinyl sulfonate.

20           4. The aqueous emulsion according to claim 1, wherein the acidic ethylenically unsaturated monomer from (A) is a phosphoric acid group selected from the group consisting of styrene phosphoric acid, sodium vinyl

phosphonate, and  $\text{CH}_2=\text{C}(\text{CH}_3)\text{COO}(\text{CH}_2)_n\text{OPO}_3\text{H}$ , wherein  $n$  is from 2 to 4.

5        5. The aqueous emulsion according to claim 1, wherein the ethylenically unsaturated monomer from (B) is (i)  $\text{CH}_2=\text{C}(\text{R}_1)\text{COR}_2$ , wherein  $\text{R}_1$  is methyl and  $\text{R}_2$  is  $-\text{OZ}'$ , wherein  $\text{Z}'$  is an alkyl group having from 1 to 4 carbon atoms.

10       6. The aqueous emulsion according to claim 1, wherein the ethylenically unsaturated monomer from (B) is (ii)  $\text{R}_3\text{OOC}-\text{CH}=\text{CH}-\text{COOR}_4$ , wherein  $\text{R}_3$  and  $\text{R}_4$  are independently an alkyl group having from 1 to 4 carbon atoms.

15       7. The aqueous emulsion according to claim 1, wherein the ethylenically unsaturated monomer from (B) is (iii)  $\text{CH}_2=\text{C}(\text{R}_5)\text{OCOR}_6$ , wherein  $\text{R}_5$  is methyl and  $\text{R}_6$  is an alkyl group having from 1 to 4 carbon atoms.

20       8. The aqueous emulsion according to claim 1, wherein the ethylenically unsaturated monomer from (B) is (iv)  $\text{CH}_2=\text{C}(\text{COOR}_7)\text{CH}_2\text{COOR}_8$ , wherein  $\text{R}_7$  and  $\text{R}_8$  are independently an alkyl group having from 1 to 4 carbon atoms.



9. The aqueous emulsion according to claim 1, wherein the ethylenically unsaturated monomer from (B) is (v)  $\text{CH}_3\text{CH}=\text{CHCOOR}_9$ , wherein  $\text{R}_9$  is an alkyl group having from 1 to 4 carbon atoms.

5 10. The aqueous emulsion according to claim 1, wherein the ethylenically unsaturated monomer from (B) is (vi) styrene.


11. The aqueous emulsion according to claim 1, wherein the ethylenically unsaturated monomer from (B) is (vii)  $\text{R}_{12}\text{CH}=\text{CHR}_{13}$ , wherein  
10  $\text{R}_{12}$  and  $\text{R}_{13}$  are independently hydrogen or methyl.

12. An aqueous emulsion comprising a water-dispersible copolymer which is non-dispersible in aqueous solutions containing 0.5% or more of an inorganic salt, wherein the water-dispersible copolymer  
15 comprises in percentages by weight:

(A) from about 10% to about 90% of an acidic ethylenically unsaturated monomer; and

(B) from about 10% to about 90% of an ethylenically unsaturated monomer selected from the group of monomer formulas consisting of:

- 20 (i)  $\text{CH}_2=\text{C}(\text{R}'_1)\text{COR}'_2$ ;  
(ii)  $\text{R}'_3\text{OOC}-\text{CH}=\text{CH}-\text{COOR}'_4$ ;  
(iii)  $\text{CH}_2=\text{C}(\text{R}'_5)\text{OCOR}'_6$ ;



5 wherein  $\text{R}'_1$  is hydrogen or methyl, and  $\text{R}'_2$  is selected from the group consisting of  $-\text{OZ}'$ ,  $-\text{N}(\text{Z}'')(\text{Z}'')$ , and  $-\text{OZ}'''\text{OH}$ , wherein  $\text{Z}'$  is an alkyl group having from 8 to 18 carbon atoms;  $\text{Z}''$  is independently selected from the group consisting of alkyl groups having from 7 to 10 carbon atoms, dimethylamino alkyl groups having from 1 to 5 carbon atoms, and  
 10 hydroxyalkyl groups having from 1 to 5 carbon atoms; and  $\text{Z}'''$  is an alkyl group having from 1 to 4 carbon atoms;  $\text{R}'_3$  and  $\text{R}'_4$  are independently an alkyl group having from 8 to 18 carbon atoms;  $\text{R}'_5$  is hydrogen or methyl and  $\text{R}'_6$  is an alkyl group having from 8 to 18 carbon atoms;  $\text{R}'_7$  and  $\text{R}'_8$  are independently an alkyl group having from 8 to 18 carbon atoms;  $\text{R}'_9$  is an  
 15 alkyl group having from 8 to 18 carbon atoms;  $\text{R}'_{10}$  and  $\text{R}'_{11}$  are independently an alkyl group having from 1 to 2 carbon atoms;  $\text{R}'_{12}$  and  $\text{R}'_{13}$  are independently selected from the group consisting of 2-pyrrolidinone, N-caprolactam, 2-pyridine, 3-pyridine, 4-pyridine, and an alkyl group having from 7 to 18 carbon atoms, with the proviso that  $\text{R}_{12}$  and  $\text{R}_{13}$  are not at the  
 20 same time 2-pyrrolidinone, N-caprolactam, 2-pyridine, 3-pyridine, or 4-pyridine; and the copolymer has a weight average molecular weight greater than about 25,000 and is present in an amount from about 20% to about 70%.

13. The aqueous emulsion according to claim 12, wherein the acidic ethylenically unsaturated monomer from (A) is a carboxylic acid group selected from the group consisting of acrylic acid, methacrylic acid, maleic acid, maleic acid half esters, maleic anhydride, itaconic acid, and crotonic acid.

14. The aqueous emulsion according to claim 12, wherein the acidic ethylenically unsaturated monomer from (A) is a sulfonic acid group selected from the group consisting of styrene sulfonic acid, 2-acrylamido-2-methylpropane sulfonic acid, and sodium vinyl sulfonate.

15. The aqueous emulsion according to claim 12, wherein the acidic ethylenically unsaturated monomer from (A) is a phosphoric acid group selected from the group consisting of styrene phosphoric acid, sodium vinyl phosphonate, and  $\text{CH}_2=\text{C}(\text{CH}_3)\text{COO}(\text{CH}_2)_n\text{OPO}_3\text{H}$ , wherein  $n$  is from 2 to 4.

16. The aqueous emulsion according to claim 12, wherein the ethylenically unsaturated monomer from (B) is (i)  $\text{CH}_2=\text{C}(\text{R}'_1)\text{COR}'_2$ , wherein  $\text{R}'_1$  is methyl,  $\text{R}'_2$  is selected from the group consisting of  $-\text{OZ}'$ ,  $-\text{N}(\text{Z}'')(\text{Z}''')$ , and  $-\text{OZ}'''\text{OH}$ , wherein  $\text{Z}'$  is an alkyl group having from 8 to 12 carbon atoms;  $\text{Z}''$  is independently selected from the group consisting of alkyl groups

having from 8 to 10 carbon atoms, dimethylamino alkyl groups having from 1 to 3 carbon atoms, and hydroxyalkyl groups having from 1 to 3 carbon atoms; and Z''' is an alkyl group having from 1 to 2 carbon atoms.

5           17. The aqueous emulsion according to claim 12, wherein the ethylenically unsaturated monomer from (B) is (ii)  $R'_3OOC-CH=CH-COOR'_4$ , wherein  $R'_3$  and  $R'_4$  are independently an alkyl group having from 8 to 12 carbon atoms.

10           18. The aqueous emulsion according to claim 12, wherein the ethylenically unsaturated monomer from (B) is (iii)  $CH_2=C(R'_5)OCOR'_6$ , wherein  $R'_5$  is methyl, and  $R'_6$  is an alkyl group having from 8 to 12 carbon atoms.

15           19. The aqueous emulsion according to claim 12, wherein the ethylenically unsaturated monomer from (B) is (iv)  $CH_2=C(COOR'_7)CH_2COOR'_8$ , wherein  $R'_7$  and  $R'_8$  are independently an alkyl group having from 8 to 12 carbon atoms.

20           20. The aqueous emulsion according to claim 12, wherein the ethylenically unsaturated monomer from (B) is (v)  $CH_3CH=CHCOOR'_9$ , and  $R'_9$  is an alkyl group having from 8 to 12 carbon atoms.

21. The aqueous emulsion according to claim 12, wherein the ethylenically unsaturated monomer from (B) is (vi)  $R'_{10}C_6H_4CR'_{11}=CHR'_{11}$ , and  $R'_{10}$  and  $R'_{11}$  are independently methyl.

5

22. The aqueous emulsion according to claim 12, wherein the ethylenically unsaturated monomer from (B) is (vii)  $R'_{12}CH=CHR'_{13}$ , wherein  $R'_{12}$  and  $R'_{13}$  are independently selected from the group consisting of 2-pyrrolidinone, N-caprolactam, 2-pyridine, 3-pyridine, 4-pyridine, and an alkyl group having from 7 to 12 carbon atoms.

10


23. An aqueous emulsion comprising a water-dispersible copolymer which is non-dispersible in aqueous solutions containing 0.5% or more of an inorganic salt, wherein the water-dispersible copolymer comprises in percentages by weight:



15

(A) from about 10% to about 80% of an acidic ethylenically unsaturated monomer, with the proviso that the acidic ethylenically unsaturated monomer is not acrylic acid;

(B) from about 10% to about 80% of an ethylenically unsaturated monomer selected from the group of monomer formulas consisting of:




20






wherein  $\text{R}_1$  is hydrogen or methyl and  $\text{R}_2$  is  $-\text{OZ}'$  or  $-\text{N}(\text{Z}'')(\text{Z}''')$ , wherein  $\text{Z}'$  is an alkyl group having from 1 to 7 carbon atoms, and  $\text{Z}''$  is independently selected from the group consisting of hydrogen and alkyl groups having from 1 to 6 carbon atoms;  $\text{R}_3$  and  $\text{R}_4$  are independently hydrogen or an alkyl group having from 1 to 7 carbon atoms, with the proviso that  $\text{R}_3$  and  $\text{R}_4$  are not both hydrogen;  $\text{R}_5$  is hydrogen or methyl and  $\text{R}_6$  is an alkyl group having from 1 to 7 carbon atoms;  $\text{R}_7$  and  $\text{R}_8$  are independently hydrogen or an alkyl group having from 1 to 7 carbon atoms, with the proviso that  $\text{R}_7$  and  $\text{R}_8$  are not both hydrogen;  $\text{R}_9$  is an alkyl group having from 1 to 7 carbon atoms;  $\text{R}_{10}$  and  $\text{R}_{11}$  are hydrogen; and  $\text{R}_{12}$  and  $\text{R}_{13}$  are independently selected from the group consisting of hydrogen,  $-\text{CN}$ ,  $-\text{NHCHO}$ , and an alkyl group having from 1 to 7 carbon atoms; and

(C) from about 10% to about 80% of an ethylenically unsaturated monomer selected from the group of monomer formulas consisting of:





5 wherein  $\text{R}'_1$  is hydrogen or methyl, and  $\text{R}'_2$  is selected from the group consisting of  $-\text{OZ}'$ ,  $-\text{N}(\text{Z}'')(\text{Z}''')$ , and  $-\text{OZ}'''\text{OH}$ , wherein  $\text{Z}'$  is an alkyl group having from 8 to 18 carbon atoms;  $\text{Z}''$  is independently selected from the group consisting of alkyl groups having from 7 to 10 carbon atoms, dimethylamino alkyl groups having from 1 to 5 carbon atoms, and  
 10 hydroxyalkyl groups having from 1 to 5 carbon atoms; and  $\text{Z}'''$  is an alkyl group having from 1 to 4 carbon atoms;  $\text{R}'_3$  and  $\text{R}'_4$  are independently an alkyl group having from 8 to 18 carbon atoms;  $\text{R}'_5$  is hydrogen or methyl and  $\text{R}'_6$  is an alkyl group having from 8 to 18 carbon atoms;  $\text{R}'_7$  and  $\text{R}'_8$  are independently an alkyl group having from 8 to 18 carbon atoms;  $\text{R}'_9$  is an  
 15 alkyl group having from 8 to 18 carbon atoms;  $\text{R}'_{10}$  and  $\text{R}'_{11}$  are independently an alkyl group having from 1 to 2 carbon atoms;  $\text{R}'_{12}$  and  $\text{R}'_{13}$  are independently selected from the group consisting of 2-pyrrolidinone, N-caprolactam, and an alkyl group having from 7 to 18 carbon atoms, with the proviso that  $\text{R}_{12}$  and  $\text{R}_{13}$  are not both 2-pyrrolidinone, are not both N-caprolactam, or are not a mixture thereof; and the copolymer has a weight  
 20 average molecular weight greater than about 25,000 and is present in an amount from about 20% to about 70%.

24. The aqueous emulsion according to claim 23, wherein the  
acidic ethylenically unsaturated monomer from (A) is a carboxylic acid group  
selected from the group consisting of methacrylic acid, maleic acid, maleic  
5 acid half esters, maleic anhydride, itaconic acid, and crotonic acid.

25. The aqueous emulsion according to claim 23, wherein the  
acidic ethylenically unsaturated monomer from (A) is a sulfonic acid group  
selected from the group consisting of styrene sulfonic acid, 2-acrylamido-2-  
10 methylpropane sulfonic acid, and sodium vinyl sulfonate.

26. The aqueous emulsion according to claim 23, wherein the  
acidic ethylenically unsaturated monomer from (A) is a phosphoric acid  
group selected from the group consisting of styrene phosphoric acid, sodium  
15 vinyl phosphonate, and  $\text{CH}_2=\text{C}(\text{CH}_3)\text{COO}(\text{CH}_2)_n\text{OPO}_3\text{H}$ , wherein n is from 2  
to 4.

27. The aqueous emulsion according to claim 23, wherein the  
ethylenically unsaturated monomer from (B) is (i)  $\text{CH}_2=\text{C}(\text{R}_1)\text{COR}_2$ , wherein  
20  $\text{R}_1$  is methyl and  $\text{R}_2$  is  $-\text{OZ}'$ , wherein  $\text{Z}'$  is an alkyl group having from 1 to 4  
carbon atoms.



28. The aqueous emulsion according to claim 23, wherein the ethylenically unsaturated monomer from (B) is (ii)  $R_3OOC-CH=CH-COOR_4$ , wherein  $R_3$  and  $R_4$  are independently an alkyl group having from 2 to 4 carbon atoms.

5

29. The aqueous emulsion according to claim 23, wherein the ethylenically unsaturated monomer from (B) is (iii)  $CH_2=C(R_5)OCOR_6$ , wherein  $R_5$  is methyl and  $R_6$  is an alkyl group having from 1 to 4 carbon atoms.

10

30. The aqueous emulsion according to claim 23, wherein the ethylenically unsaturated monomer from (B) is (iv)  $CH_2=C(COOR_7)CH_2COOR_8$ , wherein  $R_7$  and  $R_8$  are independently an alkyl group having from 2 to 4 carbon atoms.

15

31. The aqueous emulsion according to claim 23, wherein the ethylenically unsaturated monomer from (B) is (v)  $CH_3CH=CHCOOR_9$ , wherein  $R_9$  is an alkyl group having from 2 to 4 carbon atoms.

20

32. The aqueous emulsion according to claim 23, wherein the ethylenically unsaturated monomer from (B) is (vi)  $R_{10}C_6H_4CR_{11}=CHR_{11}$ , wherein  $R_{10}$  and  $R_{11}$  are hydrogen.

33. The aqueous emulsion according to claim 23, wherein the ethylenically unsaturated monomer from (B) is (vii)  $R_{12}CH=CHR_{13}$ , wherein  $R_{12}$  and  $R_{13}$  are independently hydrogen or methyl.

5

34. The aqueous emulsion according to claim 23, wherein the ethylenically unsaturated monomer from (C) is (i)  $CH_2=C(R'_1)COR'_2$ , wherein  $R'_1$  is methyl,  $R'_2$  is selected from the group consisting of  $-OZ'$ ,  $-N(Z'')(Z''')$ , and  $-OZ'''OH$ , wherein  $Z'$  is an alkyl group having from 8 to 12 carbon atoms;  $Z''$  is independently selected from the group consisting of alkyl groups having from 8 to 10 carbon atoms, dimethylamino alkyl groups having from 1 to 3 carbon atoms, and hydroxyalkyl groups having from 1 to 3 carbon atoms; and  $Z'''$  is an alkyl group having from 1 to 2 carbon atoms.

10

35. The aqueous emulsion according to claim 23, wherein the ethylenically unsaturated monomer from (C) is (ii)  $R'_3OOC-CH=CH-COOR'_4$ , wherein  $R'_3$  and  $R'_4$  are independently an alkyl group having from 8 to 12 carbon atoms.

15

36. The aqueous emulsion according to claim 23, wherein the ethylenically unsaturated monomer from (C) is (iii)  $CH_2=C(R'_5)OCOR'_6$ , wherein  $R'_5$  is methyl, and  $R'_6$  is an alkyl group having from 8 to 12 carbon atoms.

20

37. The aqueous emulsion according to claim 23, wherein the ethylenically unsaturated monomer from (C) is (iv)  $\text{CH}_2=\text{C}(\text{COOR}'_7)\text{CH}_2\text{COOR}'_8$ , wherein  $\text{R}'_7$  and  $\text{R}'_8$  are independently an alkyl group having from 8 to 12 carbon atoms.

38. The aqueous emulsion according to claim 23, wherein the ethylenically unsaturated monomer from (C) is (v)  $\text{CH}_3\text{CH}=\text{CHCOOR}'_9$ , and  $\text{R}'_9$  is an alkyl group having from 8 to 12 carbon atoms.

10

39. The aqueous emulsion according to claim 23, wherein the ethylenically unsaturated monomer from (C) is (vi)  $\text{R}'_{10}\text{C}_6\text{H}_4\text{CR}'_{11}=\text{CHR}'_{11}$ , and  $\text{R}'_{10}$  and  $\text{R}'_{11}$  have 1 carbon atom.

15

40. The aqueous emulsion according to claim 23, wherein the ethylenically unsaturated monomer from (C) is (vii)  $\text{R}'_{12}\text{CH}=\text{CHR}'_{13}$ , wherein  $\text{R}'_{12}$  and  $\text{R}'_{13}$  are independently selected from the group consisting of 2-pyrrolidinone, N-caprolactam, and an alkyl group having from 7 to 12 carbon atoms.




20

41. A method for preparing an aqueous emulsion comprising a water-dispersible copolymer which is non-dispersible in aqueous solutions containing 0.5% or more of an inorganic salt, comprising the steps of:

(a) providing the following monomers in percentages by weight;

(A) from about 10% to about 90% of an acidic ethylenically unsaturated monomer; and

(B) from about 10% to about 90% of an ethylenically unsaturated monomer selected from the group of monomer formulas consisting of:



wherein  $\text{R}_1$  is hydrogen or methyl and  $\text{R}_2$  is  $-\text{OZ}'$  or  $-\text{N}(\text{Z}'')(\text{Z}''')$ , wherein  $\text{Z}'$  is an alkyl group having from 1 to 7 carbon atoms, and  $\text{Z}''$  is independently selected from the group consisting of hydrogen and alkyl groups having from 1 to 6 carbon atoms;  $\text{R}_3$  and  $\text{R}_4$  are independently hydrogen or an alkyl group having from 1 to 7 carbon atoms, with the proviso that  $\text{R}_3$  and  $\text{R}_4$  are not both hydrogen;  $\text{R}_5$  is hydrogen or methyl and  $\text{R}_6$  is an alkyl group having from 1 to 7 carbon atoms;  $\text{R}_7$  and  $\text{R}_8$  are independently hydrogen or an alkyl group having from 1 to 7 carbon atoms, with the proviso that  $\text{R}_7$  and  $\text{R}_8$  are not both hydrogen;  $\text{R}_9$  is an alkyl group having from 1 to 7 carbon atoms;  $\text{R}_{10}$  and  $\text{R}_{11}$  are hydrogen;  $\text{R}_{12}$  and  $\text{R}_{13}$  are independently selected from the group consisting of hydrogen,  $-\text{CN}$ ,  $-\text{NHCHO}$ ,  $-\text{NHCOCH}_3$ , and an alkyl

group having from 1 to 7 carbon atoms; and the copolymer has a weight average molecular weight greater than about 25,000 and is present in an amount from about 20% to about 70%; and

(b) emulsion polymerizing the monomers from (A) and (B) in water at a solids level from about 20% to about 70% in the presence of a surfactant.

42. The method according to claim 41, wherein the acidic ethylenically unsaturated monomer from (A) is selected from the group consisting of acrylic acid, methacrylic acid, maleic acid, maleic acid half esters, maleic anhydride, itaconic acid, crotonic acid, styrene sulfonic acid, 2-acrylamido-2-methylpropane sulfonic acid, sodium vinyl sulfonate, styrene phosphoric acid, sodium vinyl phosphonate, and  $\text{CH}_2=\text{C}(\text{CH}_3)\text{COO}(\text{CH}_2)_n\text{OPO}_3\text{H}$ , wherein n is from 2 to 4.

15

43. The method according to claim 41, wherein the ethylenically unsaturated monomer from (B) is selected from the group consisting of:

- (i)  $\text{CH}_2=\text{C}(\text{R}_1)\text{COR}_2$ , wherein  $\text{R}_1$  is methyl and  $\text{R}_2$  is  $-\text{OZ}'$ , wherein  $\text{Z}'$  is an alkyl group having from 1 to 4 carbon atoms;
- (ii)  $\text{R}_3\text{OOC}-\text{CH}=\text{CH}-\text{COOR}_4$ , wherein  $\text{R}_3$  and  $\text{R}_4$  are independently an alkyl group having from 1 to 4 carbon atoms;
- (iii)  $\text{CH}_2=\text{C}(\text{R}_5)\text{OCOR}_6$ , wherein  $\text{R}_5$  is methyl and  $\text{R}_6$  is an alkyl group having from 1 to 4 carbon atoms;

- (iv)  $\text{CH}_2=\text{C}(\text{COOR}_7)\text{CH}_2\text{COOR}_8$ , wherein  $\text{R}_7$  and  $\text{R}_8$  are independently an alkyl group having from 1 to 4 carbon atoms;
- (v)  $\text{CH}_3\text{CH}=\text{CHCOOR}_9$ , wherein  $\text{R}_9$  is an alkyl group having from 1 to 4 carbon atoms;
- 5 (vi) styrene; and
- (vii)  $\text{R}_{12}\text{CH}=\text{CHR}_{13}$ , wherein  $\text{R}_{12}$  and  $\text{R}_{13}$  are independently hydrogen or methyl.

44. A method for preparing an aqueous emulsion comprising a  
10 water-dispersible copolymer which is non-dispersible in aqueous solutions containing 0.5% or more of an inorganic salt, comprising the steps of:

(a) providing the following monomers in percentages by weight;

(A) from about 10% to about 90% of an acidic ethylenically unsaturated monomer; and

15 (B) from about 10% to about 90% of an ethylenically unsaturated monomer selected from the group of monomer formulas consisting of:

(i)  $\text{CH}_2=\text{C}(\text{R}_1)\text{COR}_2$ ;

(ii)  $\text{R}_3\text{OOC}-\text{CH}=\text{CH}-\text{COOR}_4$ ;

(iii)  $\text{CH}_2=\text{C}(\text{R}_5)\text{OCOR}_6$ ;

20 (iv)  $\text{CH}_2=\text{C}(\text{COOR}_7)\text{CH}_2\text{COOR}_8$ ;

(v)  $\text{CH}_3\text{CH}=\text{CHCOOR}_9$ ;

(vi)  $\text{R}_{10}\text{C}_6\text{H}_4\text{CR}_{11}=\text{CHR}_{11}$ ; and

(vii)  $R_{12}CH=CHR_{13}$ ;

wherein  $R_1$  is hydrogen or methyl and  $R_2$  is  $-OZ'$  or  $-N(Z'')(Z''')$ , wherein  $Z'$  is an alkyl group having from 1 to 7 carbon atoms, and  $Z''$  is independently selected from the group consisting of hydrogen and alkyl groups having from  
5 1 to 6 carbon atoms;  $R_3$  and  $R_4$  are independently hydrogen or an alkyl group having from 1 to 7 carbon atoms, with the proviso that  $R_3$  and  $R_4$  are not both hydrogen;  $R_5$  is hydrogen or methyl and  $R_6$  is an alkyl group having from 1 to 7 carbon atoms;  $R_7$  and  $R_8$  are independently hydrogen or an alkyl group having from 1 to 7 carbon atoms, with the proviso that  $R_7$  and  $R_8$  are  
10 not both hydrogen;  $R_9$  is an alkyl group having from 1 to 7 carbon atoms;  $R_{10}$  and  $R_{11}$  are hydrogen;  $R_{12}$  and  $R_{13}$  are independently selected from the group consisting of hydrogen,  $-CN$ ,  $-NHCHO$ ,  $-NHCOCH_3$ , and an alkyl group having from 1 to 7 carbon atoms; and the copolymer has a weight average molecular weight greater than about 25,000 and is present in an  
15 amount from about 20% to about 70%; and

(b) neutralizing the monomers from (A) and (B) in water to a level from about 2% to about 15% molar of the acidic ethylenically unsaturated monomer from (A); and

(c) emulsion polymerizing the monomers from (A) and (B) at a  
20 solids level from about 20% to about 70% without a surfactant.

45. The method according to claim 44, wherein the acidic ethylenically unsaturated monomer from (A) is selected from the group

consisting of acrylic acid, methacrylic acid, maleic acid, maleic acid half esters, maleic anhydride, itaconic acid, crotonic acid, styrene sulfonic acid, 2-acrylamido-2-methylpropane sulfonic acid, sodium vinyl sulfonate, styrene phosphoric acid, sodium vinyl phosphonate, and  
 5  $\text{CH}_2=\text{C}(\text{CH}_3)\text{COO}(\text{CH}_2)_n\text{OPO}_3\text{H}$ , wherein n is from 2 to 4.

46. The method according to claim 44, wherein the ethylenically unsaturated monomer from (B) is selected from the group consisting of:

- (i)  $\text{CH}_2=\text{C}(\text{R}_1)\text{COR}_2$ , wherein  $\text{R}_1$  is methyl and  $\text{R}_2$  is  $-\text{OZ}'$ , wherein  $\text{Z}'$  is an alkyl group having from 1 to 4 carbon atoms;
- (ii)  $\text{R}_3\text{OOC}-\text{CH}=\text{CH}-\text{COOR}_4$ , wherein  $\text{R}_3$  and  $\text{R}_4$  are independently an alkyl group having from 1 to 4 carbon atoms;
- (iii)  $\text{CH}_2=\text{C}(\text{R}_5)\text{OCOR}_6$ , wherein  $\text{R}_5$  is methyl and  $\text{R}_6$  is an alkyl group having from 1 to 4 carbon atoms;
- 15 (iv)  $\text{CH}_2=\text{C}(\text{COOR}_7)\text{CH}_2\text{COOR}_8$ , wherein  $\text{R}_7$  and  $\text{R}_8$  are independently an alkyl group having from 1 to 4 carbon atoms;
- (v)  $\text{CH}_3\text{CH}=\text{CHCOOR}_9$ , wherein  $\text{R}_9$  is an alkyl group having from 1 to 4 carbon atoms;
- (vi) styrene; and
- 20 (vii)  $\text{R}_{12}\text{CH}=\text{CHR}_{13}$ , wherein  $\text{R}_{12}$  and  $\text{R}_{13}$  are independently hydrogen or methyl.



47. A method for preparing an aqueous emulsion comprising a water-dispersible copolymer which is non-dispersible in aqueous solutions containing 0.5% or more of an inorganic salt, comprising the steps of:

(a) providing the following monomers in percentages by weight;

5 (A) from about 10% to about 90% of an acidic ethylenically unsaturated monomer; and

(B) from about 10% to about 90% of an ethylenically unsaturated monomer selected from the group of monomer formulas consisting of:

(i)  $\text{CH}_2=\text{C}(\text{R}'_1)\text{COR}'_2$ ;

10 (ii)  $\text{R}'_3\text{OOC}-\text{CH}=\text{CH}-\text{COOR}'_4$ ;

(iii)  $\text{CH}_2=\text{C}(\text{R}'_5)\text{OCOR}'_6$ ;

(iv)  $\text{CH}_2=\text{C}(\text{COOR}'_7)\text{CH}_2\text{COOR}'_8$ ;

(v)  $\text{CH}_3\text{CH}=\text{CHCOOR}'_9$ ;

(vi)  $\text{R}'_{10}\text{C}_6\text{H}_4\text{CR}'_{11}=\text{CHR}'_{11}$ ; and

15 (vii)  $\text{R}'_{12}\text{CH}=\text{CHR}'_{13}$ ;

wherein  $\text{R}'_1$  is hydrogen or methyl, and  $\text{R}'_2$  is selected from the group consisting of  $-\text{OZ}'$ ,  $-\text{N}(\text{Z}'')(\text{Z}'')$ , and  $-\text{OZ}'''\text{OH}$ , wherein  $\text{Z}'$  is an alkyl group having from 8 to 18 carbon atoms;  $\text{Z}''$  is independently selected from the group consisting of alkyl groups having from 7 to 10 carbon atoms, dimethylamino alkyl groups having from 1 to 5 carbon atoms, and hydroxyalkyl groups having from 1 to 5 carbon atoms; and  $\text{Z}'''$  is an alkyl group having from 1 to 4 carbon atoms;  $\text{R}'_3$  and  $\text{R}'_4$  are independently an alkyl group having from 8 to 18 carbon atoms;  $\text{R}'_5$  is hydrogen or methyl and

20

R'<sub>6</sub> is an alkyl group having from 8 to 18 carbon atoms; R'<sub>7</sub> and R'<sub>8</sub> are independently an alkyl group having from 8 to 18 carbon atoms; R'<sub>9</sub> is an alkyl group having from 8 to 18 carbon atoms; R'<sub>10</sub> and R'<sub>11</sub> are independently an alkyl group having from 1 to 2 carbon atoms; R'<sub>12</sub> and R'<sub>13</sub> are independently selected from the group consisting of 2-pyrrolidinone, N-caprolactam, 2-pyridine, 3-pyridine, 4-pyridine, and an alkyl group having from 7 to 18 carbon atoms, with the proviso that R<sub>12</sub> and R<sub>13</sub> are not at the same time 2-pyrrolidinone, N-caprolactam, 2-pyridine, 3-pyridine, or 4-pyridine; and the copolymer has a weight average molecular weight greater than about 25,000 and is present in an amount from about 20% to about 70%; and

(b) emulsion polymerizing the monomers from (A) and (B) in water at a solids level from about 20% to about 70% in the presence of a surfactant.

15

48. The method according to claim 47, wherein the acidic ethylenically unsaturated monomer from (A) is selected from the group consisting of acrylic acid, methacrylic acid, maleic acid, maleic acid half esters, maleic anhydride, itaconic acid, crotonic acid, styrene sulfonic acid, 2-acrylamido-2-methylpropane sulfonic acid, sodium vinyl sulfonate, styrene phosphoric acid, sodium vinyl phosphonate, and  $\text{CH}_2=\text{C}(\text{CH}_3)\text{COO}(\text{CH}_2)_n\text{OPO}_3\text{H}$ , wherein n is from 2 to 4.

20

49. The method according to claim 47, wherein the ethylenically unsaturated monomer from (B) is selected from the group consisting of:
- (i)  $\text{CH}_2=\text{C}(\text{R}'_1)\text{COR}'_2$ , wherein  $\text{R}'_1$  is methyl,  $\text{R}'_2$  is selected from the group consisting of  $-\text{OZ}'$ ,  $-\text{N}(\text{Z}'')(\text{Z}'')$ , and  $-\text{OZ}'''\text{OH}$ , wherein  $\text{Z}'$  is an alkyl group having from 8 to 12 carbon atoms;  $\text{Z}''$  is independently selected from the group consisting of alkyl groups having from 8 to 10 carbon atoms, dimethylamino alkyl groups having from 1 to 3 carbon atoms, and hydroxyalkyl groups having from 1 to 3 carbon atoms; and  $\text{Z}'''$  is an alkyl group having from 1 to 2 carbon atoms;
  - (ii)  $\text{R}'_3\text{OOC}-\text{CH}=\text{CH}-\text{COOR}'_4$ , wherein  $\text{R}'_3$  and  $\text{R}'_4$  are independently an alkyl group having from 8 to 12 carbon atoms;
  - (iii)  $\text{CH}_2=\text{C}(\text{R}'_5)\text{OCOR}'_6$ , wherein  $\text{R}'_5$  is methyl, and  $\text{R}'_6$  is an alkyl group having from 8 to 12 carbon atoms;
  - (iv)  $\text{CH}_2=\text{C}(\text{COOR}'_7)\text{CH}_2\text{COOR}'_8$ , wherein  $\text{R}'_7$  and  $\text{R}'_8$  are independently an alkyl group having from 8 to 12 carbon atoms;
  - (v)  $\text{CH}_3\text{CH}=\text{CHCOOR}'_9$ , and  $\text{R}'_9$  is an alkyl group having from 8 to 12 carbon atoms;
  - (vi)  $\text{R}'_{10}\text{C}_6\text{H}_4\text{CR}'_{11}=\text{CHR}'_{11}$ , and  $\text{R}'_{10}$  and  $\text{R}'_{11}$  are independently methyl; and
  - (vii)  $\text{R}'_{12}\text{CH}=\text{CHR}'_{13}$ , wherein  $\text{R}'_{12}$  and  $\text{R}'_{13}$  are independently selected from the group consisting of 2-pyrrolidinone, N-caprolactam, 2-pyridine, 3-pyridine, 4-pyridine, and an alkyl group having from 7 to 12 carbon atoms.

50. A method for preparing an aqueous emulsion comprising a water-dispersible copolymer which is non-dispersible in aqueous solutions containing 0.5% or more of an inorganic salt, comprising the steps of:

- 5 (a) providing the following monomers in percentages by weight;
- (A) from about 10% to about 90% of an acidic ethylenically unsaturated monomer; and
- (B) from about 10% to about 90% of an ethylenically unsaturated monomer selected from the group of monomer formulas consisting of:
- 10 (i)  $\text{CH}_2=\text{C}(\text{R}'_1)\text{COR}'_2$ ;
- (ii)  $\text{R}'_3\text{OOC}-\text{CH}=\text{CH}-\text{COOR}'_4$ ;
- (iii)  $\text{CH}_2=\text{C}(\text{R}'_5)\text{OCOR}'_6$ ;
- (iv)  $\text{CH}_2=\text{C}(\text{COOR}'_7)\text{CH}_2\text{COOR}'_8$ ;
- (v)  $\text{CH}_3\text{CH}=\text{CHCOOR}'_9$ ;
- 15 (vi)  $\text{R}'_{10}\text{C}_6\text{H}_4\text{CR}'_{11}=\text{CHR}'_{11}$ ; and
- (vii)  $\text{R}'_{12}\text{CH}=\text{CHR}'_{13}$ ;

wherein  $\text{R}'_1$  is hydrogen or methyl, and  $\text{R}'_2$  is selected from the group consisting of  $-\text{OZ}'$ ,  $-\text{N}(\text{Z}'')(\text{Z}'')$ , and  $-\text{OZ}'''\text{OH}$ , wherein  $\text{Z}'$  is an alkyl group having from 8 to 18 carbon atoms;  $\text{Z}''$  is independently selected from the

20 group consisting of alkyl groups having from 7 to 10 carbon atoms, dimethylamino alkyl groups having from 1 to 5 carbon atoms, and hydroxyalkyl groups having from 1 to 5 carbon atoms; and  $\text{Z}'''$  is an alkyl group having from 1 to 4 carbon atoms;  $\text{R}'_3$  and  $\text{R}'_4$  are independently an

alkyl group having from 8 to 18 carbon atoms; R'<sub>5</sub> is hydrogen or methyl and R'<sub>6</sub> is an alkyl group having from 8 to 18 carbon atoms; R'<sub>7</sub> and R'<sub>8</sub> are independently an alkyl group having from 8 to 18 carbon atoms; R'<sub>9</sub> is an alkyl group having from 8 to 18 carbon atoms; R'<sub>10</sub> and R'<sub>11</sub> are  
5 independently an alkyl group having from 1 to 2 carbon atoms; R'<sub>12</sub> and R'<sub>13</sub> are independently selected from the group consisting of 2-pyrrolidinone, N-caprolactam, 2-pyridine, 3-pyridine, 4-pyridine, and an alkyl group having from 7 to 18 carbon atoms, with the proviso that R<sub>12</sub> and R<sub>13</sub> are not at the same time 2-pyrrolidinone, N-caprolactam, 2-pyridine, 3-pyridine, or 4-  
10 pyridine; and the copolymer has a weight average molecular weight greater than about 25,000 and is present in an amount from about 20% to about 70%; and

(b) neutralizing the monomers from (A) and (B) in water to a level from about 2% to about 15% molar of the acidic ethylenically unsaturated  
15 monomer from (A); and

(c) emulsion polymerizing the monomers from (A) and (B) at a solids level from about 20% to about 70% without a surfactant.

51. The method according to claim 50, wherein the acidic  
20 ethylenically unsaturated monomer from (A) is selected from the group consisting of acrylic acid, methacrylic acid, maleic acid, maleic acid half esters, maleic anhydride, itaconic acid, crotonic acid, styrene sulfonic acid, 2-acrylamido-2-methylpropane sulfonic acid, sodium vinyl sulfonate, styrene

phosphoric acid, sodium vinyl phosphonate, and  $\text{CH}_2=\text{C}(\text{CH}_3)\text{COO}(\text{CH}_2)_n\text{OPO}_3\text{H}$ , wherein  $n$  is from 2 to 4.

52. The method according to claim 50, wherein the ethylenically unsaturated monomer from (B) is selected from the group consisting of:
- (i)  $\text{CH}_2=\text{C}(\text{R}'_1)\text{COR}'_2$ , wherein  $\text{R}'_1$  is methyl,  $\text{R}'_2$  is selected from the group consisting of  $-\text{OZ}'$ ,  $-\text{N}(\text{Z}'')(\text{Z}''')$ , and  $-\text{OZ}'''\text{OH}$ , wherein  $\text{Z}'$  is an alkyl group having from 8 to 12 carbon atoms;  $\text{Z}''$  is independently selected from the group consisting of alkyl groups having from 8 to 10 carbon atoms, dimethylamino alkyl groups having from 1 to 3 carbon atoms, and hydroxyalkyl groups having from 1 to 3 carbon atoms; and  $\text{Z}'''$  is an alkyl group having from 1 to 2 carbon atoms;
  - (ii)  $\text{R}'_3\text{OOC}-\text{CH}=\text{CH}-\text{COOR}'_4$ , wherein  $\text{R}'_3$  and  $\text{R}'_4$  are independently an alkyl group having from 8 to 12 carbon atoms;
  - (iii)  $\text{CH}_2=\text{C}(\text{R}'_5)\text{OCOR}'_6$ , wherein  $\text{R}'_5$  is methyl, and  $\text{R}'_6$  is an alkyl group having from 8 to 12 carbon atoms;
  - (iv)  $\text{CH}_2=\text{C}(\text{COOR}'_7)\text{CH}_2\text{COOR}'_8$ , wherein  $\text{R}'_7$  and  $\text{R}'_8$  are independently an alkyl group having from 8 to 12 carbon atoms;
  - (v)  $\text{CH}_3\text{CH}=\text{CHCOOR}'_9$ , and  $\text{R}'_9$  is an alkyl group having from 8 to 12 carbon atoms;
  - (vi)  $\text{R}'_{10}\text{C}_6\text{H}_4\text{CR}'_{11}=\text{CHR}'_{11}$ , and  $\text{R}'_{10}$  and  $\text{R}'_{11}$  are independently methyl; and
  - (vii)  $\text{R}'_{12}\text{CH}=\text{CHR}'_{13}$ , wherein  $\text{R}'_{12}$  and  $\text{R}'_{13}$  are independently selected from the group consisting of 2-pyrrolidinone, N-caprolactam, 2-pyridine, 3-


pyridine, 4-pyridine, and an alkyl group having from 7 to 12 carbon atoms.

53. A method for preparing an aqueous emulsion comprising a water-dispersible copolymer which is non-dispersible in aqueous solutions containing 0.5% or more of an inorganic salt, comprising the steps of:

(a) providing the following monomers in percentages by weight;

(A) from about 10% to about 80% of an acidic ethylenically unsaturated monomer;

(B) from about 10% to about 80% of an ethylenically unsaturated monomer selected from the group of monomer formulas consisting of:



wherein  $\text{R}_1$  is hydrogen or methyl and  $\text{R}_2$  is  $-\text{OZ}'$  or  $-\text{N}(\text{Z}'')(\text{Z}''')$ , wherein  $\text{Z}'$  is an alkyl group having from 1 to 7 carbon atoms, and  $\text{Z}''$  is independently selected from the group consisting of hydrogen and alkyl groups having from 1 to 6 carbon atoms;  $\text{R}_3$  and  $\text{R}_4$  are independently hydrogen or an alkyl group having from 1 to 7 carbon atoms, with the proviso that  $\text{R}_3$  and  $\text{R}_4$  are not both hydrogen;  $\text{R}_5$  is hydrogen or methyl and  $\text{R}_6$  is an alkyl group having

from 1 to 7 carbon atoms;  $R_7$  and  $R_8$  are independently hydrogen or an alkyl group having from 1 to 7 carbon atoms, with the proviso that  $R_7$  and  $R_8$  are not both hydrogen;  $R_9$  is an alkyl group having from 1 to 7 carbon atoms;  $R_{10}$  and  $R_{11}$  are hydrogen; and  $R_{12}$  and  $R_{13}$  are independently selected from the group consisting of hydrogen, -CN, -NHCHO, and an alkyl group having from 1 to 7 carbon atoms; and

(C) from about 10% to about 80% of an ethylenically unsaturated monomer selected from the group of monomer formulas consisting of:

- (i)  $\text{CH}_2=\text{C}(\text{R}'_1)\text{COR}'_2$ ;
- (ii)  $\text{R}'_3\text{OOC}-\text{CH}=\text{CH}-\text{COOR}'_4$ ;
- (iii)  $\text{CH}_2=\text{C}(\text{R}'_5)\text{OCOR}'_6$ ;
- (iv)  $\text{CH}_2=\text{C}(\text{COOR}'_7)\text{CH}_2\text{COOR}'_8$ ;
- (v)  $\text{CH}_3\text{CH}=\text{CHCOOR}'_9$ ;
- (vi)  $\text{R}'_{10}\text{C}_6\text{H}_4\text{CR}'_{11}=\text{CHR}'_{11}$ ; and
- (vii)  $\text{R}'_{12}\text{CH}=\text{CHR}'_{13}$ ;

wherein  $\text{R}'_1$  is hydrogen or methyl, and  $\text{R}'_2$  is selected from the group consisting of -OZ', -N(Z'')(Z''), and -OZ'''OH, wherein Z' is an alkyl group having from 8 to 18 carbon atoms; Z'' is independently selected from the group consisting of alkyl groups having from 7 to 10 carbon atoms, dimethylamino alkyl groups having from 1 to 5 carbon atoms, and hydroxyalkyl groups having from 1 to 5 carbon atoms; and Z''' is an alkyl group having from 1 to 4 carbon atoms;  $\text{R}'_3$  and  $\text{R}'_4$  are independently an alkyl group having from 8 to 18 carbon atoms;  $\text{R}'_5$  is hydrogen or methyl and



R'<sub>6</sub> is an alkyl group having from 8 to 18 carbon atoms; R'<sub>7</sub> and R'<sub>8</sub> are independently an alkyl group having from 8 to 18 carbon atoms; R'<sub>9</sub> is an alkyl group having from 8 to 18 carbon atoms; R'<sub>10</sub> and R'<sub>11</sub> are independently an alkyl group having from 1 to 2 carbon atoms; R'<sub>12</sub> and R'<sub>13</sub> are independently selected from the group consisting of 2-pyrrolidinone, N-caprolactam, and an alkyl group having from 7 to 18 carbon atoms, with the proviso that R<sub>12</sub> and R<sub>13</sub> are not both 2-pyrrolidinone, are not both N-caprolactam, or are not a mixture thereof; and the copolymer has a weight average molecular weight greater than about 25,000 and is present in an amount from about 20% to about 70%; and

(b) emulsion polymerizing the monomers from (A), (B), and (C) in water at a solids level from about 20% to about 70% in the presence of a surfactant.

54. The method according to claim 53, wherein the acidic ethylenically unsaturated monomer from (A) is selected from the group consisting of acrylic acid, methacrylic acid, maleic acid, maleic acid half esters, maleic anhydride, itaconic acid, crotonic acid, styrene sulfonic acid, 2-acrylamido-2-methylpropane sulfonic acid, sodium vinyl sulfonate, styrene phosphoric acid, sodium vinyl phosphonate, and  $\text{CH}_2=\text{C}(\text{CH}_3)\text{COO}(\text{CH}_2)_n\text{OPO}_3\text{H}$ , wherein n is from 2 to 4.

55. The method according to claim 53, wherein the ethylenically unsaturated monomer from (B) is selected from the group consisting of:

- (i)  $\text{CH}_2=\text{C}(\text{R}_1)\text{COR}_2$ , wherein  $\text{R}_1$  is methyl and  $\text{R}_2$  is  $-\text{OZ}'$ , wherein  $\text{Z}'$  is an alkyl group having from 1 to 4 carbon atoms;
- 5 (ii)  $\text{R}_3\text{OOC}-\text{CH}=\text{CH}-\text{COOR}_4$ , wherein  $\text{R}_3$  and  $\text{R}_4$  are independently an alkyl group having from 1 to 4 carbon atoms;
- (iii)  $\text{CH}_2=\text{C}(\text{R}_5)\text{OCOR}_6$ , wherein  $\text{R}_5$  is methyl and  $\text{R}_6$  is an alkyl group having from 1 to 4 carbon atoms;
- (iv)  $\text{CH}_2=\text{C}(\text{COOR}_7)\text{CH}_2\text{COOR}_8$ , wherein  $\text{R}_7$  and  $\text{R}_8$  are independently an  
10 alkyl group having from 1 to 4 carbon atoms;
- (v)  $\text{CH}_3\text{CH}=\text{CHCOOR}_9$ , wherein  $\text{R}_9$  is an alkyl group having from 1 to 4 carbon atoms;
- (vi) styrene; and
- (vii)  $\text{R}_{12}\text{CH}=\text{CHR}_{13}$ , wherein  $\text{R}_{12}$  and  $\text{R}_{13}$  are independently hydrogen or  
15 methyl.

56. The method according to claim 53, wherein the ethylenically unsaturated monomer from (C) is selected from the group consisting of:

- (i)  $\text{CH}_2=\text{C}(\text{R}'_1)\text{COR}'_2$ , wherein  $\text{R}'_1$  is methyl,  $\text{R}'_2$  is selected from the group  
20 consisting of  $-\text{OZ}'$ ,  $-\text{N}(\text{Z}'')(\text{Z}''')$ , and  $-\text{OZ}'''\text{OH}$ , wherein  $\text{Z}'$  is an alkyl group having from 8 to 12 carbon atoms;  $\text{Z}''$  is independently selected from the group consisting of alkyl groups having from 8 to 10 carbon atoms, dimethylamino alkyl groups having from 1 to 3 carbon atoms, and

- hydroxyalkyl groups having from 1 to 3 carbon atoms; and Z''' is an alkyl group having from 1 to 2 carbon atoms;
- (ii)  $R'_3OOC-CH=CH-COOR'_4$ , wherein  $R'_3$  and  $R'_4$  are independently an alkyl group having from 8 to 12 carbon atoms;
- 5 (iii)  $CH_2=C(R'_5)OCOR'_6$ , wherein  $R'_5$  is methyl, and  $R'_6$  is an alkyl group having from 8 to 12 carbon atoms;
- (iv)  $CH_2=C(COOR'_7)CH_2COOR'_8$ , wherein  $R'_7$  and  $R'_8$  are independently an alkyl group having from 8 to 12 carbon atoms;
- (v)  $CH_3CH=CHCOOR'_9$ , and  $R'_9$  is an alkyl group having from 8 to 12 carbon
- 10 atoms;
- (vi)  $R'_{10}C_6H_4CR'_{11}=CHR'_{11}$ , and  $R'_{10}$  and  $R'_{11}$  are independently methyl; and
- (vii)  $R'_{12}CH=CHR'_{13}$ , wherein  $R'_{12}$  and  $R'_{13}$  are independently selected from the group consisting of 2-pyrrolidinone, N-caprolactam, 2-pyridine, 3-pyridine, 4-pyridine, and an alkyl group having from 7 to 12 carbon atoms.

15

57. A method for preparing an aqueous emulsion comprising a water-dispersible copolymer which is non-dispersible in aqueous solutions containing 0.5% or more of an inorganic salt, comprising the steps of:

(a) providing the following monomers in percentages by weight;

20 (A) from about 10% to about 80% of an acidic ethylenically unsaturated monomer;



(B) from about 10% to about 80% of an ethylenically unsaturated monomer selected from the group of monomer formulas consisting of:

- (i)  $\text{CH}_2=\text{C}(\text{R}_1)\text{COR}_2$ ;
- (ii)  $\text{R}_3\text{OOC}-\text{CH}=\text{CH}-\text{COOR}_4$ ;
- (iii)  $\text{CH}_2=\text{C}(\text{R}_5)\text{OCOR}_6$ ;
- (iv)  $\text{CH}_2=\text{C}(\text{COOR}_7)\text{CH}_2\text{COOR}_8$ ;
- 5 (v)  $\text{CH}_3\text{CH}=\text{CHCOOR}_9$ ;
- (vi)  $\text{R}_{10}\text{C}_6\text{H}_4\text{CR}_{11}=\text{CHR}_{11}$ ; and
- (vii)  $\text{R}_{12}\text{CH}=\text{CHR}_{13}$ ;

wherein  $\text{R}_1$  is hydrogen or methyl and  $\text{R}_2$  is  $-\text{OZ}'$  or  $-\text{N}(\text{Z}'')(\text{Z}''')$ , wherein  $\text{Z}'$  is an alkyl group having from 1 to 7 carbon atoms, and  $\text{Z}''$  is independently  
 10 selected from the group consisting of hydrogen and alkyl groups having from 1 to 6 carbon atoms;  $\text{R}_3$  and  $\text{R}_4$  are independently hydrogen or an alkyl group having from 1 to 7 carbon atoms, with the proviso that  $\text{R}_3$  and  $\text{R}_4$  are not both hydrogen;  $\text{R}_5$  is hydrogen or methyl and  $\text{R}_6$  is an alkyl group having from 1 to 7 carbon atoms;  $\text{R}_7$  and  $\text{R}_8$  are independently hydrogen or an alkyl  
 15 group having from 1 to 7 carbon atoms, with the proviso that  $\text{R}_7$  and  $\text{R}_8$  are not both hydrogen;  $\text{R}_9$  is an alkyl group having from 1 to 7 carbon atoms;  $\text{R}_{10}$  and  $\text{R}_{11}$  are hydrogen; and  $\text{R}_{12}$  and  $\text{R}_{13}$  are independently selected from the group consisting of hydrogen,  $-\text{CN}$ ,  $-\text{NHCHO}$ , and an alkyl group having from 1 to 7 carbon atoms; and

20 (C) from about 10% to about 80% of an ethylenically unsaturated monomer selected from the group of monomer formulas consisting of:

- (i)  $\text{CH}_2=\text{C}(\text{R}'_1)\text{COR}'_2$ ;



wherein  $R'_1$  is hydrogen or methyl, and  $R'_2$  is selected from the group consisting of  $-OZ'$ ,  $-N(Z'')(Z'')$ , and  $-OZ'''OH$ , wherein  $Z'$  is an alkyl group having from 8 to 18 carbon atoms;  $Z''$  is independently selected from the group consisting of alkyl groups having from 7 to 10 carbon atoms, dimethylamino alkyl groups having from 1 to 5 carbon atoms, and hydroxyalkyl groups having from 1 to 5 carbon atoms; and  $Z'''$  is an alkyl group having from 1 to 4 carbon atoms;  $R'_3$  and  $R'_4$  are independently an alkyl group having from 8 to 18 carbon atoms;  $R'_5$  is hydrogen or methyl and  $R'_6$  is an alkyl group having from 8 to 18 carbon atoms;  $R'_7$  and  $R'_8$  are independently an alkyl group having from 8 to 18 carbon atoms;  $R'_9$  is an alkyl group having from 8 to 18 carbon atoms;  $R'_{10}$  and  $R'_{11}$  are independently an alkyl group having from 1 to 2 carbon atoms;  $R'_{12}$  and  $R'_{13}$  are independently selected from the group consisting of 2-pyrrolidinone, N-caprolactam, and an alkyl group having from 7 to 18 carbon atoms, with the proviso that  $R'_{12}$  and  $R'_{13}$  are not both 2-pyrrolidinone, are not both N-caprolactam, or are not a mixture thereof; and the copolymer has a weight average molecular weight greater than about 25,000 and is present in an

amount from about 20% to about 70%; and

(b) neutralizing the monomers from (A), (B), and (C) in water to a level from about 2% to about 15% molar of the acidic ethylenically unsaturated monomer from (A); and

5 (c) emulsion polymerizing the monomers from (A), (B), and (C) at a solids level from about 20% to about 70% without a surfactant.

58. The method according to claim 57, wherein the acidic ethylenically unsaturated monomer from (A) is selected from the group  
10 consisting of acrylic acid, methacrylic acid, maleic acid, maleic acid half esters, maleic anhydride, itaconic acid, crotonic acid, styrene sulfonic acid, 2-acrylamido-2-methylpropane sulfonic acid, sodium vinyl sulfonate, styrene phosphoric acid, sodium vinyl phosphonate, and  $\text{CH}_2=\text{C}(\text{CH}_3)\text{COO}(\text{CH}_2)_n\text{OPO}_3\text{H}$ , wherein n is from 2 to 4.

15

59. The method according to claim 57, wherein the ethylenically unsaturated monomer from (B) is selected from the group consisting of:

(i)  $\text{CH}_2=\text{C}(\text{R}_1)\text{COR}_2$ , wherein  $\text{R}_1$  is methyl and  $\text{R}_2$  is  $-\text{OZ}'$ , wherein  $\text{Z}'$  is an alkyl group having from 1 to 4 carbon atoms;

20 (ii)  $\text{R}_3\text{OOC}-\text{CH}=\text{CH}-\text{COOR}_4$ , wherein  $\text{R}_3$  and  $\text{R}_4$  are independently an alkyl group having from 1 to 4 carbon atoms;

(iii)  $\text{CH}_2=\text{C}(\text{R}_5)\text{OCOR}_6$ , wherein  $\text{R}_5$  is methyl and  $\text{R}_6$  is an alkyl group having from 1 to 4 carbon atoms;

- (iv)  $\text{CH}_2=\text{C}(\text{COOR}_7)\text{CH}_2\text{COOR}_8$ , wherein  $\text{R}_7$  and  $\text{R}_8$  are independently an alkyl group having from 1 to 4 carbon atoms;
- (v)  $\text{CH}_3\text{CH}=\text{CHCOOR}_9$ , wherein  $\text{R}_9$  is an alkyl group having from 1 to 4 carbon atoms;
- 5 (vi) styrene; and
- (vii)  $\text{R}_{12}\text{CH}=\text{CHR}_{13}$ , wherein  $\text{R}_{12}$  and  $\text{R}_{13}$  are independently hydrogen or methyl.

60. The method according to claim 57, wherein the ethylenically  
 10 unsaturated monomer from (C) is selected from the group consisting of:

- (i)  $\text{CH}_2=\text{C}(\text{R}'_1)\text{COR}'_2$ , wherein  $\text{R}'_1$  is methyl,  $\text{R}'_2$  is selected from the group consisting of  $-\text{OZ}'$ ,  $-\text{N}(\text{Z}'')(\text{Z}'')$ , and  $-\text{OZ}'''\text{OH}$ , wherein  $\text{Z}'$  is an alkyl group having from 8 to 12 carbon atoms;  $\text{Z}''$  is independently selected from the group consisting of alkyl groups having from 8 to 10 carbon atoms,  
 15 dimethylamino alkyl groups having from 1 to 3 carbon atoms, and hydroxyalkyl groups having from 1 to 3 carbon atoms; and  $\text{Z}'''$  is an alkyl group having from 1 to 2 carbon atoms;
- (ii)  $\text{R}'_3\text{OOC}-\text{CH}=\text{CH}-\text{COOR}'_4$ , wherein  $\text{R}'_3$  and  $\text{R}'_4$  are independently an alkyl group having from 8 to 12 carbon atoms;
- 20 (iii)  $\text{CH}_2=\text{C}(\text{R}'_5)\text{OCOR}'_6$ , wherein  $\text{R}'_5$  is methyl, and  $\text{R}'_6$  is an alkyl group having from 8 to 12 carbon atoms;
- (iv)  $\text{CH}_2=\text{C}(\text{COOR}'_7)\text{CH}_2\text{COOR}'_8$ , wherein  $\text{R}'_7$  and  $\text{R}'_8$  are independently an alkyl group having from 8 to 12 carbon atoms;

(v)  $\text{CH}_3\text{CH}=\text{CHCOOR}'_9$ , and  $\text{R}'_9$  is an alkyl group having from 8 to 12 carbon atoms;

(vi)  $\text{R}'_{10}\text{C}_6\text{H}_4\text{CR}'_{11}=\text{CHR}'_{11}$ , and  $\text{R}'_{10}$  and  $\text{R}'_{11}$  are independently methyl; and

(vii)  $\text{R}'_{12}\text{CH}=\text{CHR}'_{13}$ , wherein  $\text{R}'_{12}$  and  $\text{R}'_{13}$  are independently selected from  
5 the group consisting of 2-pyrrolidinone, N-caprolactam, 2-pyridine, 3-pyridine, 4-pyridine, and an alkyl group having from 7 to 12 carbon atoms.



## INTERNATIONAL SEARCH REPORT

International application No.

PCT/US01/09833

**A. CLASSIFICATION OF SUBJECT MATTER**

IPC(7) : Please See Extra Sheet.

US CL : Please See Extra Sheet.

According to International Patent Classification (IPC) or to both national classification and IPC

**B. FIELDS SEARCHED**

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 524/547, 548, 555, 556, 558, 559, 808, 812, 814, 815, 816, 817, 819, 820, 823, 824, 832, 833

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EAST

**C. DOCUMENTS CONSIDERED TO BE RELEVANT**

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 4,151,143 A (BLANK et al.) 24 April 1979, the ABSTRACT, col. 2, lines 9-68, col. 3, lines 1-68 and col. 4, lines 1-42.	1, 2, 5-13, 16-21, 23, 24, 27-39, 41-46, 50-52 and 57-60
X	US 4,522,972 A (MONDT et al) 11 June 1985, the ABSTRACT, col. 2, lines 18-64, col. 3, lines 24-68, col. 4, lines 10-34 and col. 5, lines 44-65.	1, 2, 5-13, 16-21, 23, 24, 27-39, 41-43, 47-49 and 53-56

☒ Further documents are listed in the continuation of Box C.
 ☐ See patent family annex.

* Special categories of cited documents:	
"A" document defining the general state of the art which is not considered to be of particular relevance	"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
"E" earlier document published on or after the international filing date	"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
"O" document referring to an oral disclosure, use, exhibition or other means	"&" document member of the same patent family
"P" document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search 25 JUNE 2001	Date of mailing of the international search report 24 AUG 2001
Name and mailing address of the ISA/US Commissioner of Patents and Trademarks Box PCT Washington, D.C. 20231 Facsimile No. (703) 305-3230	Authorized officer JUDY M. REDDICK Telephone No. (703) 308-0651 <i>Russ Well</i>

# INTERNATIONAL SEARCH REPORT

International application No.  
PCT/US01/09333

C (Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5,356,968 A (RUPANER et al) 18 October 1994, the ABSTRACT, col. 2, lines 18-68, col. 3, lines 1-68, col. 4, lines 1-68, col. 5, lines 1-63, col. 6, lines 1-68, col. 7, lines 1-66, col. 8, lines 1-23, col. 10, lines 1-68, col. 11, lines 1-20, and col. 12, lines 1-59.	1-60
X	US 5,631,317 A (KOMATSU) 20 May 1997, the Abstract, col. 3, lines 32-51, col. 4, lines 1-44.	1-40, 44-46, 50-52 and 57-60

## INTERNATIONAL SEARCH REPORT

In: International application No.  
PCT/US01/09333

### A. CLASSIFICATION OF SUBJECT MATTER:

IPC (7): C08L 25/02, 25/14, 31/02, 31/04, 33/02, 33/04, 39/00, 39/08

### A. CLASSIFICATION OF SUBJECT MATTER:

US CL: 524/547, 548, 555, 556, 558, 559, 808, 812, 814, 815, 816, 817, 819, 820, 823, 824, 832, 833

**THIS PAGE BLANK (USPTO)**

**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

**BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☒ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☒ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**

**THIS PAGE BLANK (USPTO)**